

Issued Date :
 Oct 12, 2020

Effective Date :
 Jan 26, 2021

Properties/Test Method	Specificaton	Unit
PA80010 - Carbon (LOI)	Min 80	%
PA80010 - Ash	Max 20	%
PA80012 - Moisture	Max 2	%
PA80013 - Volatile	Max 4	%
Particle Size Distribution		
PA80017 - Alpine -50 Mesh	Min 100	%
PA80017 - Alpine -100 Mesh	Min 99	%
PA80017 - Alpine -200 Mesh	Min 90--Max 98	%
PA80017 - Alpine -325 Mesh	Min 30--Max 80	%

This Specification Sheet is provided for informational purposes. Superior Graphite makes no express or implied representation or warranty regarding the accuracy of the information set forth in this Specification Sheet or regarding any Superior Graphite product or the use thereof (including without limitation, any warranty of quality, merchantability, or fitness for a particular use or purpose), except to the extent otherwise expressly provided in Superior Graphite's Terms and Conditions of Sale. Each customer of Superior Graphite assumes all risk and liability relating to its use of Superior Graphite's products and is responsible for independently testing Superior Graphite's products prior to such customer's use thereof to determine whether such products are fit and suitable for such customer's intended use or purpose. This Specification Sheet is subject to change upon written notice.

Superior Graphite

10 S. Riverside Plaza, Suite 1470
 Chicago, Illinois 60606 USA
 P +1 312 559 2999 | +1 800 325 0337
 F +1 312 559 9064
 CustomerServiceUSA@SuperiorGraphite.com

Superior Graphite Europe Ltd.

Box 1300, SE-85013
 Sundsvall, Sweden
 P +46 60 13 4118
 F +46 60 13 4128
 CustomerServiceEU@SuperiorGraphite.com

**Superior Graphite Import & Export
 (Shanghai) Co. Ltd.**

Room 821, No. 4229 Bao'an Road
 Jiading District, Shanghai 201814, P.R. China
 P +86 21 595 800 75, Ext. 103
 F +86 21 595 800 76
 CustomerServiceChina@SuperiorGraphite.com

