

CYMEL[®] U-1050-10 resin

PRODUCT DESCRIPTION

CYMEL U-1050-10 resin is a partially n-butylated urea resin supplied in n-butanol and is the HAPS compliant version of CYMEL U-1050 resin. CYMEL U-1050-10 resin has wide compatibility with other film formers and is useful in fast curing industrial baking finishes and low temperature curing conversion varnishes for wood.

BENEFITS

- Fast curing
- Wide range of compatibility

APPLICATION AREAS

- Exempt solvent systems
- Fast-curing baking enamels
- Low temperature curing conversion varnishes
- Epoxy ester primers
- Grinding vehicle

PHYSICAL PROPERTIES

Property	Range	Method
Appearance	Clear Liquid	Visual
Non-volatile by wt.	60 ± 2%	Pan, 2 hrs/105°C
Viscosity, 25°C	Z-Z ₂	Gardner-Holdt
Free formaldehyde	≤ 3.0%	Sulfite Method
Color, Gardner	< 1	

SOLUBILITY

Alcohols	Complete
Esters	Complete
Ketones	Complete
Aromatic hydrocarbons	Complete
Aliphatic hydrocarbons	Partial
Water	Insoluble

COMPATIBILITY

Acrylic resins	Good
Alkyd resins	Very good
Polyester resins	Very good
Epoxy resins	Good

BACKBONE POLYMER SELECTION

CYMEL U-1050-10 resin is a very effective crosslinking agent for backbone polymer resins containing hydroxyl, carboxyl, and amide functional groups, such as those found on alkyd, polyester or acrylic resins. CYMEL U-1050-10 resin has a high reactivity and a high tendency for self-condensation providing fast drying films with very good gloss, hardness, stackability and adhesion properties. Although the optimum level of CYMEL U-1050-10 resin in a given formulation should be determined experimentally, ratios of 25-35%, based on resin solids, are typically most effective over a range of polymer backbone resins.

CATALYSIS

In baking enamels, CYMEL U-1050-10 resin does not need the addition of an acid catalyst to the formulation to obtain effective cure. In many instances, the acidity of the backbone polymer in the formulation is sufficient to catalyze the reaction. If catalyst addition is required, then 0.5 - 1.0% of CYCAT[®] 4040 catalyst based on total resin solids is recommended for baking schedules of ~125°C for 15 minutes. For wood coating formulations, 6 - 10% Cypat 4040 catalyst on total resin solids of the formulation is sufficient to obtain fast drying behavior at room temperature.

FORMULATION STABILITY

The stability of baking enamels containing CYMEL U-1050-10 resin can be enhanced by the addition of alcohols, amines or combination of these. Low molecular weight primary alcohols, such as n-butanol, are most effective. Recommended amines are TEA, DMEA or 2-AMP at a concentration of 0.5-1.0% on total binder solids. Ambient cure systems are usually stabilized only by addition of adequate amounts of primary alcohol, such as ethanol or butanol.

STORAGE STABILITY

CYMEL U-1050-10 resin has a shelf life of 48 months from date of manufacture when stored at temperatures between 5°C and 30°C. Although low temperatures are not detrimental to stability, the viscosity of the product will increase making the resin more difficult to pump or pour. Product viscosity can be returned to normal by gentle re-warming, however, care should be taken to avoid excessive localized heating as this can cause polymerization.

• Worldwide Contact Info: www.allnex.com •

Disclaimer: Allnex Group companies ("Allnex") decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents Allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of Allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any Allnex and/or third party intellectual property rights. The user should perform its own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of Allnex and/or third parties remains the sole responsibility of the user.

Notice: Trademarks indicated with the ®, ™ or * are registered, unregistered or pending trademarks of Allnex Belgium SA or its directly or indirectly affiliated Allnex Group companies.

January 2015