

EBECRYL® 225

Aliphatic Urethane Acrylate

September 2017



INTRODUCTION

EBECRYL 225 is a ten functional aliphatic urethane acrylate. After polymerization, films of EBECRYL 225 exhibit outstanding surface hardness and low haze development after abrasion. In addition, EBECRYL 225 does not contain intentionally added organic tin compounds, heavy metals* or quinones.

PERFORMANCE HIGHLIGHTS

EBECRYL 225 is characterized by:

- Light color
- Liquid at room temperature
- Regulation friendly for tin, heavy metals*, and quinones (*Please note that quinones are present in many raw materials, so the overall quinone content is reduced, but not zero in EBECRYL 225*)

UV/EB cured products containing EBECRYL 225 are characterized by the following performance properties:

- Outstanding hardness
- Outstanding scratch and abrasion resistance
- Outstanding steel wool (0000) scratch resistance
- Excellent cure response

The actual properties of UV/EB cured products also depend on the selection of other formulation components such as reactive diluents, additives and photoinitiators.

SUGGESTED APPLICATIONS

Formulated UV/EB curable products containing EBECRYL 225 may be applied via brush, roller, direct or reverse roll, offset gravure, metering rod, slot die, knife over roll, air knife, curtain, immersion and spin coating methods, as well as screen printing. EBECRYL 225 is recommended for use:

- Hard coatings for plastics and optical films
- In applications that must meet regulations for tin, heavy metal*, and quinone content.
- As an additive to improve cure speed, solvent resistance, scratch resistance and abrasion resistance.
- In clear and pigmented coatings for paper, paperboard, wood, rigid plastics, filmic substrates.

SPECIFICATIONS

	VALUE
Appearance	Clear liquid
Color, Pt-Co scale ⁽¹⁾ , max.	150
NCO, %, max.	0.08
Viscosity, 60°C, cP/mPa-s	1800-2500

TYPICAL PHYSICAL PROPERTIES


Density, g/ml at 25°C ⁽²⁾	1.19
Functionality, theoretical ⁽³⁾	10

TYPICAL CURED PROPERTIES⁽⁴⁾

Tensile strength, psi (MPa)	2100 (14.5)
Elongation at break, %	0.8
Young's Modulus, psi (MPa)	395000 (2700)

GRAPH I

EBECRYL 225 - VISCOSITY REDUCTION WITH REACTIVE DILUENTS



*As defined by C.O.N.E.G's Toxic in Packaging Legislation, the ASTM Standard Consumer Safety Specification on Toy Safety F 963 (ASTM F 963-08), or the European Standard on Safety of Toys EN 71 Part 3 : 1994 + A1:2000 + A1/AC:2000 + AC:2002

(1) Also referred to as APHA or Hazen color.
 (2) Typical property. Not measured.
 (3) Theoretical determination based on the undiluted oligomer.
 (4) UV cured 125 µ thick films.


VISCOSITY REDUCTION

Graph I shows the viscosity reduction of EBECRYL 225 with 1,6-hexanediol diacrylate (HDDA)⁽¹⁾, isobornyl acrylate (IBOA)⁽¹⁾, trimethylolpropane triacrylate (TMPTA)⁽¹⁾, and butyl acetate. Although viscosity reduction can be achieved with non-reactive solvents, reactive diluents are preferred because they are essentially 100 percent converted during UV/EB exposure to form a part of the coating or ink, thus reducing solvent emissions. The specific reactive diluents used will influence performance properties such as hardness and flexibility.

Graph II illustrates the change in viscosity of EBECRYL 225 with increasing temperature.

GRAPH II

EBECRYL 225 - VISCOSITY VS. TEMPERATURE



(1) Product of allnex.

www.allnex.com

Disclaimer: allnex Group companies ("allnex") decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any allnex and/or third party intellectual property rights. The user should perform his/her own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of allnex and/or third parties remains the sole responsibility of the user.

Notice: Trademarks indicated with ®, ™ or * as well as the allnex name and logo are registered, unregistered or pending trademarks of Allnex IP s.à.r.l. or its directly or indirectly affiliated allnex Group companies.

PRECAUTIONS

Before using EBECRYL 225, see the Safety Data Sheet (SDS) for information on the identified hazards of the material and the recommended personal protective equipment and procedures.

STORAGE AND HANDLING

Care should be taken not to expose the product to high temperature conditions, direct sunlight, ignition sources, oxidizing agents, alkalis or acids. This might cause uncontrollable polymerization of the product with the generation of heat. Storage and handling should be in stainless steel, amber glass, amber polyethylene or baked phenolic lined containers. Procedures that remove or displace oxygen from the material should be avoided. Do not store this material under an oxygen free atmosphere. Dry air is recommended to displace material removed from the container. Wash thoroughly after handling. Keep container tightly closed. Use with adequate ventilation.

See the SDS for the recommended storage temperature range for EBECRYL 225.

Please refer to the allnex Guide to Safety and Handling of Acrylate Oligomers and Monomers for additional information on the safe handling of acrylates.