

# EBECRYL® 871

Lithographic Ink Varnish

March 2017



## INTRODUCTION

EBECRYL 871 is an energy curable polyester acrylate. This varnish was developed for use in lithographic inks, and can be used in both the pigment dispersion and letdown portions of the ink. Inks made with EBECRYL 871 exhibit good color development and excellent printability.

## PERFORMANCE HIGHLIGHTS

- Excellent pigment wetting
- Good water balance
- Excellent printability
- Good reactivity
- Low misting

## SUGGESTED APPLICATIONS

EBECRYL 871 is recommended for wet or dry offset inks. It is compatible with other polyester or epoxy acrylates and can be used in conjunction with specialty polyesters such as EBECRYL 436 and 438 to promote adhesion to plastics and provide film integrity.

## TYPICAL TACK RANGES<sup>(1)</sup>

Oligomer / Reactive diluent	Tack, g-m
EBECRYL 871	12-14
EBECRYL 871/5% OTA 480 <sup>(2)</sup>	7-11
EBECRYL 871/10% OTA 480	6-8
EBECRYL 871/5% TRPGDA <sup>(2)</sup>	7-11
EBECRYL 871/10% TRPGDA	6-8

(1) 400 RPM, 90°F, 3 minutes; Thwing-Albert Electronic Inkometer

(2) Product of allnex

(3) Theoretical determination based on the undiluted oligomer

[www.allnex.com](http://www.allnex.com)

Disclaimer: allnex Group companies ("allnex") decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any allnex and/or third party intellectual property rights. The user should perform his/her own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of allnex and/or third parties remains the sole responsibility of the user.

Notice: Trademarks indicated with ®, ™ or \* as well as the allnex name and logo are registered, unregistered or pending trademarks of Allnex IP s.à.r.l. or its directly or indirectly affiliated allnex Group companies.

## SPECIFICATIONS

	VALUE
Acid Value, mg KOH/g, max	12.5
Appearance	Clear amber liquid
Color, Gardner scale, max.	10.0
Viscosity, 25°C, cP/mPa-s	48000-57000

## TYPICAL PROPERTIES

Oligomer tack <sup>(1)</sup> , gram-meters (g-m)	12-14
Functionality, theoretical <sup>(3)</sup>	6
Density, g/ml at 25°C	1.1

## PRECAUTIONS

Before using EBECRYL 871, see the Safety Data Sheet (SDS) for information on the identified hazards of the material and the recommended personal protective equipment and procedures.

## STORAGE AND HANDLING

Care should be taken not to expose the product to high temperature conditions, direct sunlight, ignition sources, oxidizing agents, alkalis or acids. This might cause uncontrollable polymerization of the product with the generation of heat. Storage and handling should be in stainless steel, amber glass, amber polyethylene or baked phenolic lined containers. Procedures that remove or displace oxygen from the material should be avoided. Do not store this material under an oxygen free atmosphere. Dry air is recommended to displace material removed from the container. Wash thoroughly after handling. Keep container tightly closed. Use with adequate ventilation.

See the SDS for the recommended storage temperature range for EBECRYL 871.

Please refer to the allnex Guide to Safety and Handling of Acrylate Oligomers and Monomers for additional information on the safe handling of acrylates.