

Dynasylan® VTMOEO

Vinyltris(2-methoxyethoxy)silane

Technical data

Properties and test methods	Value	Unit	Method
Density (20 °C/ 68 °F)	approx. 1.040	g/cm ³	DIN 51757
Refractive index n(20, D)	approx. 1.430	-	DIN 51423
Boiling point (2,7 hPa)	approx. 108/226	°C/ °F	DIN 51356
Flash point	approx. 115/239	°C/ °F	DIN 51758
Viscosity (20 °C/ 68 °F)	approx. 2.7/2.6	mPa·s /cSt	DIN 53015

Registrations

Dynasylan® VTMOEO

ECL (South Korea):	Yes
EINECS/ELINCS (EU):	Yes
AICS (Australia):	Yes
DSL/NDSL (Canada):	Yes
PICCS (Philippines):	Yes
TSCA (USA):	Yes
IECS (P.R. China):	Yes
ENCS (Japan):	Yes

Dynasylan® VTMOEO is a bifunctional organosilane possessing a reactive vinyl group and a hydrolyzable 2-methoxy-ethoxy-silyl group.

The dual nature of its reactivity allows **Dynasylan® VTMOEO** to bind chemically to both inorganic materials (e.g. glass, metals, fillers) and organic polymers (e.g. thermosets, thermoplastics, elastomers) thus functioning mainly as an efficient adhesion promoter and/or surface modifier.

Dynasylan® VTMOEO is a colorless, low-viscosity liquid with a typical aromatic odor.

Safety and handling

Before considering the use of Dynasylan® products please read its Material Safety Data sheet (MSDS) thoroughly for safety and toxicological data as well as for information on proper transportation, storage and use. The Material Safety Data Sheet is available after registration on our website www.dynasylan.com or upon request from your local representative, customer service or from Evonik Industries AG, Product Safety Department, E-MAIL sds-im@evonik.com.

Packaging and storage

Dynasylan® VTMOEO is supplied in 25 kg containers, in 200 kg drums, or in 1.000 kg IBC one-way containers. The containers must remain tightly sealed during storage and kept in a cool, well aired place. Product should be protected against humidity. In the unopened container the shelf life of **Dynasylan® VTMOEO** is one year.

Properties and application

1. Adhesion promotion

Dynasylan[®] VTMOEO acts as an adhesion promoter for various mineral-filled polymers improving their mechanical and electrical properties, especially after exposure to moisture.

Once bonded to an inorganic filler, **Dynasylan**[®] VTMOEO hydrophobises the filler surface. This effect improves the compatibility of fillers with the polymer matrix, leading to a better dispersibility, reduced melt viscosity and easier processing of filled plastics. The principle of the adhesion promotion is shown below:

2. **Dynasylan**[®] VTMOEO as co-monomer for polymer dispersions

Polymer dispersions (e.g. styrene acrylics), modified with **Dynasylan**[®] VTMOEO show improved adhesion strength in wet conditions and wet scrub resistance.

3. Other applications

Dynasylan[®] VTMOEO can also be used as additive in organic coatings to improve adhesion on inorganic surfaces (metals, glass, ceramic surfaces), as well as for surface treatment of inorganic pigments.

Reactivity

In the presence of moisture, the methoxy-ethoxy groups of **Dynasylan**[®] VTMOEO hydrolyze to produce 2-methoxyethanol and reactive silanol (Si-OH) groups which can bond to a variety of inorganic substrates. The vinyl functional end of **Dynasylan**[®] VTMOEO can react with a suitable polymer (activated by peroxide or radiation).

Processing

Toxicological and Environmental Aspects:

When exposed to moisture **Dynasylan**[®] VTMOEO liberates 2-methoxyethanol. This alcohol is suspected to be teratogenic. Evonik Degussa offers a new generation of alternatives to vinyltris(2-methoxyethoxy)silane that do not liberate 2-methoxyethanol. In many applications these products perform even better than vinyltris(2-methoxy-ethoxy)-silane. More information about these alternatives is given in the Product Information for **Dynasylan**[®] 6490, **Dynasylan**[®] 6498 and **Dynasylan**[®] 6598.

This information and all technical and other advice are based on Evonik's present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. EVONIK DISCLAIMS ALL REPRESENTATIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, AND SHALL HAVE NO LIABILITY FOR, MERCHANTABILITY OF THE PRODUCT OR ITS FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE), OR OTHERWISE. EVONIK SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used.

Europe/Middle-East/Africa/RoW

Evonik Industries AG

Inorganic Materials
Rodenbacher Chaussee 4
63457 Hanau-Wolfgang
Germany
PHONE +49 6181 59 13636
FAX +49 6181 59 13737
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

Evonik Degussa (SEA) Pte. Ltd.

Inorganic Materials
3 Internatioanl Business Park
#07-18, Nordic European Centre
Singapore 609927
PHONE +65 6809 6830
FAX +65 6809 6630
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

Evonik Taiwan Ltd.

Inorganic Materials
Artist Construction Bldg.
9F, No. 133
Min Sheng East Road, Sec 3
Taipei, 105 Taiwan, R.O.C.
Taiwan
PHONE +886 227 17 1242
FAX +886 227 17 2106
dynasytan@evonik.com
www.dynasytan.com

North America

Evonik Degussa Corporation

Inorganic Materials
P.O. Box 677
299 Jefferson Road
Parsippany, NJ 07054-0677
USA
PHONE (TOLL FREE) +1 800 237 67 45
PHONE +1 973 929 8513
FAX +1 973 929 8503
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

Evonik Degussa (Shanghai) Co. Ltd.

Inorganic Materials
55, Chungdong Road
Shanghai 201108
P.R. China
PHONE +86 21 6119 1053
FAX +86 21 6119 1075
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

Evonik Japan Co. Ltd

Inorganic Materials
12th Floor Monolith Building
2-3-1, Nishi-Shinjuku-ku
Tokyo 163-0912
Japan
PHONE +81 353 23 7300
FAX +81 353 23 7399
dynasytan@evonik.com
www.dynasytan.com

Latin America

Evonik Brasil Ltda.

Inorganic Materials
Alameda Campinas, 579
01404-000 São Paulo-SP
Brazil
PHONE +55 11 3146 4123
FAX +55 11 3146 4109
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

Evonik Korea Ltd.

Inorganic Materials
94, Galsan 1-dong
Bupyeong-gu
Incheon, 403-081
Korea
PHONE +82 32 510 2433
FAX +82 32 505 2510
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

Evonik India Pvt. Ltd.

Inorganic Materials
Krislon House
Saki Vihar Road, Anderi (E)
Mumbai - 400 072
India
PHONE +91 226 7238 800
FAX +91 226 7238 811
dynasytan@evonik.com
www.dynasytan.com