

HIRENOL[®] PL-2000S

KOLON INDUSTRIES

High Performance Epoxy Modifier

General Description

- Low viscosity, Low volatile extender for Epoxy, Polyurethane and Acrylic
- Act as a Plasticizer, Pot-Life controller, Diluent, Modifier
- Good Color and Excellent UV-resistance
- Wide process window ; Non-toxic, Good Compatibility, Storage Stability
- Excellent Performance in Adhesion, Hardness, Water Resistance, Gloss, Toughness, Exduation, Shrinkage, Self-leveling, Trowelability,

Properties

Items	Specification	Comment
Appearance	Transparent	Eye Test
% Non-Volatile	96 Min.	105°C X 2g X 1HR
Viscosity (cps, 25°C)	1700-2300	Brookfield Viscometer
SpGr (25°C)	Check	Typically 1.02-1.04
Color (Ga. #)	4 Max.	Typically 1-2
Hydroxyl Content	Check	Typically 2.5-2.9wt%
TMPI%	20 Max.	Gas Chromatograph

Application

- Coating ; Heavy Duty, Ship Building for steel protection
- Flooring ; Self-leveling floorings, Epoxy mortar
- Wire Enamel, Priming Coats, Injections, Joint and castings, Sealants, etc...

Notice : The information and data contained herein do not constitute sales specifications. The Property values may be changed without notice. No liability, warranty or guarantee of final product performance is created by this document. It is the buy's responsibility to determine whether Kolon Industries products are appropriate for the buy's use. No freedom from any patent or other intellectual property right is granted or to be inferred. (2007)