


VERSAL YELLOW 4G



 TiO₂ 1:1



 TiO₂ 1:10

Characteristic

C. I.	Pigment Yellow 155
C. I. No.	200 310
CAS No.	68 516-73-4
Chemical Class	Disazocond

Properties

Oil Absorbtion [ml/100 g]	81
Specific Surface [m ² /g]	32
Density [g/cm ³]	1,46
Bulking Volume [l/kg]	3,5

Fastness

DOP	5
Linseed Oil	5
White Spirite	5
Xylene	4-5
Acetone	4
Butylacetate	4-5
Ethanol	4-5
Water	5
HCl 2.5%	5
NaOH 2.5%	5
Light - Full Shade	7-8
Light - 1/1	7-8
Light - 1/3	7
Weather - Full Shade	3-4
Weather - 1/1	4-5
Weather - 1/3	4
Overspray	5
Heat Resistance [°C]	260
Migration	

Application Possibilities

Printing Inks - Flexografic	●
Printing Inks - Gravure	●
Printing Inks - Offset	●
Printing Inks - Letter	●
Paints - Waterbased	●
Paints - Nitrocelulose	●
Paints - Air Drying	●
Paints - Baking Varnish	●
<input checked="" type="checkbox"/> main application <input type="checkbox"/> ----- <input type="checkbox"/> side application	