

Matting agent

ACEMATT® HK 400

DESCRIPTION

ACEMATT® HK 400 is an untreated, medium particle sized precipitated silica. It is especially recommended for pigmented systems.

KEY BENEFITS

- very low viscosity impact
- high surface smoothness
- all purpose silica

EFFECT

Matting efficiency



Transparency



Viscosity



Smoothness/Haptic



Sedimentation behavior



SUITABILITY

waterborne



solventborne



radiation-curing



2-pack coatings



high solids



pigmented coatings



clear coatings



● not suitable ● partly suitable ● suitable

TYPICAL APPLICATIONS

- General industrial coatings
- Can coatings
- Wood coatings
- Architectural paints

TECHNICAL DATA

DOA absorption	275 ml/100g
Grindometer value	27 µm
particle size, d ₅₀	6.3 µm
pH-value	6.6
specific surface area (N ₂)	200 m ² /g

RECOMMENDED ADDITION LEVEL

As supplied calculated on total formulation: 1.5 - 7.0 %

PROCESSING INSTRUCTIONS

Addition to the coating as supplied or as a predilution is possible.

HANDLING & STORAGE

For details regarding our packaging options for this product, please contact your local sales representative. Our products are inert and extremely stable chemically. However, due to their high specific surface area, they can absorb moisture and volatile organic compounds from the surrounding atmosphere. Therefore, we recommend storing the products in sealed containers in a dry, cool place, and removed from volatile organic substances. Even if a product is stored under these conditions, after a longer period it can still pick up ambient moisture over time, which could lead to its exceeding the specified moisture content. For this reason, our recommended use-by date is 24 months after date of manufacture. Products more than 24 months old should be tested for moisture content before use in order to make certain that it is still suitable for the intended application.

MSDS & REGULATORY INFORMATION



This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Resource Efficiency GmbH | Goldschmidtstraße 100, 45127 Essen, Germany | Telefon +49 201 173-2222 Telefax +49 201 173-1939 | www.coating-additives.com