

Product information

Dynasylan[®] 6598

Reactive vinyl-alkyl siloxane oligomer, ethoxy functional

Technical data				
Properties and test methods	Value	Unit	Method	
Density (20 °C/ 68 °F)	арргох. 1	g/cm³	DIN 51757	
Boiling point (1013 hPa)	> 255/ 491	°C / °F	ASTM D-1120	
SiO ₂ -content	арргох. 42	% w/w	AN-SAA 0754	
Flash point	> 70/ >158	°C / °F	DIN EN ISO 2719 (Pensky-Martens, closed-cup)	
Viscosity (20 ° C/ 68 °F)	арргох. 3-7	mPa [.] s / cSt	DIN 53015	

Registrations

AICS (Australia): No DSL/NDSL (Canada): *	
DSL/NDSL (Canada): *)
PICCS (Philippines):	S
TSCA (USA): Ye	S
IECS (P.R. China): Ye	S
ENCS (Japan): Ye	s
EINECS/ELINCS (EU): Ye	S
ECL (South Korea): Ye	S
REACH (Europe) Ex	empted
* = available on request	
· · · · · · · · · · · · · · · · · · ·	

Dynasylan[®] 6598 is an oligomeric siloxane containing vinyl, propyl and ethoxy groups.

Dynasylan[®] 6598 is a further development of Dynasylan[®] VTMOEO, vinyl-tris(2-methoxy-ethoxy)silane.

Dynasylan[®] 6598 is a colourless, nearly odorless low-viscosity liquid. Dynasylan[®] 6598 is an excellent silane compatibiliser between inorganic fillers (e.g. kaolin, MDH, ATH) and organic polymers (EPDM, EVA, PE). The application of Dynasylan[®] 6598 in mineral-filled and peroxide-crosslinked cable systems results in improved mechanical and electrical properties, especially upon exposure to moisture. The high boiling start of Dynasylan[®] 6598, together with its high flash point, gives it several advantages over monomeric silanes with respect to safety, handling and processing. From an environmental viewpoint it should be noted that the amount of released hydrolysis ethanol (VOC) is considerably less than for monomeric silanes.

Safety and handling

Before considering the use of Dynasylan[®] products please read its Safety Data Sheet (SDS) thoroughly for safety and toxicological data as well as for information on proper transportation, storage and use. The Safety Data Sheet is available after registration on our website www.dynasylan.com or upon request from your local representative, customer service or from Evonik Operations GmbH, Product Safety Department, E-MAIL sds-hu@evonik.com.

Packaging, storage and shelf life

 $\rm Dynasylan^{*}\,6598$ is supplied in 25 kg, 200 kg drums and 900 kg ibc containers.

The containers must remain tightly sealed and stored in a cool, well-ventilated place protected against moisture.

In the unopened container the shelf life of Dynasylan® 6598 is min. 12 months from delivery.

Properties and applications

Dynasylan[®] 6598 is excellent as an adhesion promoter in mineral-filled, peroxide-crosslinked compounds. The siliconfunctional ethoxy groups of Dynasylan[®] 6598 hydrolyse in the presence of moisture, which is usually present on the filler surface, forming active silanol groups. The condensation of these silanol groups with hydroxyl groups on the filler surface leads to a tight chemical bond between Dynasylan[®] 6598 and the filler. The vinyl functional end of Dynasylan[®] 6598 can be coupled to the polymer in a further reaction that runs parallel to peroxide crosslinking.

The propyl groups of Dynasylan[®] 6598 are hydrophobic and result in markedly improved electrical properties of the filled compounds, especially after exposure to water.

A major field of application for mineral-filled compounds is the cable industry. EPDM and kaolin can be processed into cable compounds through the adhesion promoting and hydrophobic effects of Dynasylan[®] 6598. It can also be used in the manufacture of halogen-free, non-toxic, environmentallyfriendly flame retardant compounds (HFFR) based on EVA or PE and ATH or MDH. In addition, Dynasylan[®] 6598 can be used in many other applications such as filler and pigment treatment, use in dispersions etc.

Typical property improvements obtained by using Dynasylan[®] 6598 in filled polymers are:

- improved filler dispersion
- increased hydrophobicity that results in improved electrical values (dielectric constant e r, electric dissipation factor tand , volume resistivity r D) especially after exposure to water/ moisture
- increase in maximum filler loading
- excellent balance between tensile strength and elongation at break at a high level
- improved heat resistance
 improvement of creep behavior at increased temperature
- improved chemical resistance
- strongly reduced tendency to stress cracking
- higher impact strength
- higher abrasion resistance
- good processability

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

Europe/Middle-East/Africa North America

Evonik Operations GmbH Silanes Business Line Rodenbacher Chaussee 4 63457 Hanau-Wolfgang Germany FAX +49 6181 59 713915 dynasylan@evonik.com www.dynasylan.com

Asia / Pacific Evonik (SEA) Pte. Ltd.

Silanes Business Line 3 Internatioanl Business Park #07-18, Nordic European Centre Singapore 609927 PHONE +65 6809 6906 FAX +65 6809 6699 dynasylan@evonik.com www.dynasylan.com

Asia / Pacific

Evonik Japan Co. Ltd Silanes Business Line 12th Floor Monolith Building 2-3-1, Nishi-Shinjuku-ku Tokyo 163-0912 Japan PHONE +81 353 23 7446 FAX +81 353 23 7397 dynasylan@evonik.com www.dynasylan.com

Evonik Corporation

Silanes Business Line 299 Jefferson Road Parsippany, NJ 07054 USA PHONE (TOLL FREE) +1 800 237 67 FAX +1 732 981 5275 45 PHONE +1 973 929 8513 dynasylan@evonik.com

Asia / Pacific **Evonik Specialty**

www.dynasylan.com

Chemicals (Shanghai) Co. Ltd. Silanes Business Line 55, Chungdong Road Xinzhuang Industry Park Shanghai 201108 P.R. China PHONE +86 21 61191-399 FAX +86 21 61191-648 dynasylan@evonik.com www.dynasylan.com

Asia / Pacific

Evonik India Pvt. Ltd. Silanes Business Line Krislon House Saki Vihar Road, Anderi (E) Mumbai - 400 072 India PHONE +91 226 7238 809 FAX +91 226 7238 811 dynasylan@evonik.com www.dynasylan.com

North America **Silbond Corporation** 9901 Sand Creek Highway Weston, MI 49289 USA PHONE +1 732 981 5004 dynasylan@evonik.com www.dynasylan.com

Asia / Pacific Evonik Korea Ltd.

Silanes Business Line 3F (Nongshim Sungmookwan B/D) 112 Yeouidaebang-Ro Dongjak-Gu Seoul, 07057 Когеа PHONE +82 2320 4773 FAX +82 2783 2520 dynasylan@evonik.com www.dynasylan.com

Region Central and South America Evonik Brasil Ltda.

Silanes Business Line Rua Arquiteto Olavo Redig de Campos, 105 Torre A - 04711-904 São Paulo- SP Brazil PHONE +55 11 3146 9627 dynasylan@evonik.com www.dynasylan.com

Asia / Pacific

Evonik Taiwan Ltd.

Silanes Business Line Artist Construction Bldg. 9F, No. 133 Min Sheng East Road, Sec 3 Taipei, 105 Taiwan, R.O.C. Taiwan 10596 PHONE +886 227 17 1242 #247 FAX +886 227 17 2106 dynasylan@evonik.com www.dynasylan.com

