

RILSAMID®

AESNO P401

ISO 16396 - PA12-P, EGHL, C22-004

Rilsamid® AESNO P401 TL resin is a natural polyamide.
This grade is plasticized and designed for tube extrusion.

Rilsamid® AESNO P401 TL resin falls into the PA12-HIPHL category according to DIN 73378.

MAIN CHARACTERISTICS

PROPERTIES	DRY / COND	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Melt Volume-Flow Rate	13 / *	cm ³ /10min	ISO 1133
Temperature	235 / *	°C	-
Load	5 / *	kg	-
MECHANICAL PROPERTIES			
Tensile Modulus	- / 360	MPa	ISO 527-1/-2
Stress at 50% Strain	- / 24	MPa	ISO 527-1/-2
Strain at Break	- / >50	%	ISO 527-1/-2
Charpy Impact Strength, +23°C	No Break / No Break	kJ/m ²	ISO 179/1eU
Charpy Impact Strength, -30°C	No Break / No Break	kJ/m ²	ISO 179/1eU
Charpy Notched Impact Strength, +23°C	46 / No Break	kJ/m ²	ISO 179/1eA
Charpy Notched Impact Strength, -30°C	4 / 8	kJ/m ²	ISO 179/1eA
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	174 / *	°C	ISO 11357-1/-3
ELECTRICAL PROPERTIES			
Dielectric (Electric) Strength	41 / -	kV/mm	IEC 60243-1
Comparative Tracking Index	600 / -	-	IEC 60112
OTHER PROPERTIES			
Water Absorption	1.2 / *	%	Sim. to ISO 62
Density	1030 / -	kg/m ³	ISO 1183

MAIN APPLICATIONS:

Tubings

PACKAGING:

This grade is delivered dried in sealed packaging (44 lb bags / 1000 lb containers) ready to be processed.

Please consult Arkema's disclaimer regarding the use of Arkema's products on
<https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

RILSAMID[®]

AESNO P401

SHELF LIFE:

Two years from the date of delivery. for any use above this limit, please refer to our technical services.

Processing conditions for extrusion :

- Typical melt temperature (Min / Recommended / Max) : 230°C / 250°C / 270°C.
- Drying time and temperature (only necessary for bags opened for more than two hours) : 4-6 hours at 80°C.

REGIONAL AVAILABILITY

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

Rilsamid[®] is a registered trademark of Arkema
© 2022 Arkema Inc. All rights reserved.

ARKEMA

rilsamid.com

Arkema Inc - High Performance Polymers

900 First Avenue
King of Prussia, PA 19406
Tel.: +1 610 205 7000
Fax: +1 610 205 7497
hpp.arkema.com

Headquarters: Arkema France

420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
Tel.: +33 1 49 00 80 80
Fax: +33 1 49 00 83 96
arkema.com