

DESCRIPTION

ZETASPERSE® 3600 is an anionic wetting and dispersing additive for waterborne formulations. Wets and stabilizes all kinds of pigments. Shows a very low influence on the chemical resistance of the coating film.

KEY BENEFITS

- low influence on chemical resistance
- outstanding viscosity reduction with titanium dioxide
- excellent for organic pigments

EFFECT**Viscosity reduction with organic pigments/carbon blacks****Color intensity/gloss with organic pigments/carbon blacks****Viscosity reduction with inorganic pigments/fillers****Color intensity/gloss with inorganic pigments/fillers****SUITABILITY**

waterborne	solventborne
●	●
2-pack 100%	radiation-curing
●	●
direct grind	resin-containing pigment concentrates
●	●
resin-free pigment concentrates	
●	

● not suitable ● partly suitable ● suitable

TYPICAL APPLICATIONS

- General industrial coatings
- Wood coatings
- Transportation coatings
- Pigment concentrates

TECHNICAL DATA

active matter content	52 %
appearance	clear, amber liquid
chemical description	aqueous solution of copolymers with groups of high pigment affinity
solvent	water
viscosity at 25 °C	Approx 500 mPas

SOLUBILITY

Water	Ethanol
●	●
TPGDA	Acetone
●	●
Butylacetate	Mineral Spirits
●	●

● not soluble ● partly soluble ● soluble

RECOMMENDED ADDITION LEVEL

As supplied calculated on inorganic pigment: 4.0 - 30.0 %
 As supplied calculated on organic pigment: 15.0 - 65.0 %
 As supplied calculated on carbon black: 30.0 - 140.0 %
 Recommended addition level for co-grind: 0.3 - 2.0 %

PROCESSING INSTRUCTIONS

Add to the grind before dispersion.

HANDLING & STORAGE

Keep containers tightly closed in a dry, cool, and well-ventilated place. Mix thoroughly before use. Product is freeze-thaw stable; if frozen, warm to 20-40°C and mix before use. Please refer to the SDS for the most current information.

MSDS & REGULATORY INFORMATION

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Resource Efficiency GmbH | Goldschmidtstraße 100, 45127 Essen, Germany | Telefon +49 201 173-2222 Telefax +49 201 173-1939 | www.coating-additives.com