



Product Information

CODE 5925

ZINC STEARATE XM POWDER HYDENSE®

Description Medium bulk density, fine white powder.

Properties	Test	Specification	Typical Property
	Assay (%ZnO)	14.0 - 16.0%	15.0%
	Free Fatty Acid (%)	1.0% max.	0.2%
	Moisture (%)	1.0% max.	0.2%
	Sieve US Std. 100 Mesh	0.2% max. retained	<0.2%
	Sieve US Std. 200 Mesh	10.0% max. retained	<10%
	Bulk Density	Report lb./ft ³	20

Features Zinc Stearate XM Powder is produced from a high quality tallow derived fatty acid for applications requiring medium density processing aid with good flow and blending characteristics, including powdered metal, thermosets and polyolefins.

Performance Consistent physical properties and medium density provide excellent blending and dispersion properties with a large variety of materials.

Relatively large particle size and medium density contributes minimally to initial viscosity in SMC mixes, allowing for good glass wet out, while providing good lubrication and surface quality in the molding process.

Engineered particle size enhances blending properties with powdered metal and imparts consistent porosity for fabrication of self-lubricating components.

Provide acid catalyst neutralization for polyolefins and very good lubrication and mold release properties in other thermoplastic applications.

Quality Control A modern, state-of-the-art plant process with strict control ensures consistent quality in chemical and mechanical properties.

Regulatory Meets FDA requirements under 21 CFR for indirect food contact applications.

Packaging Standard 40 x 50 lb. multiwall bags on stretch wrapped pallet. Bulk packaging in supersacks is available.

Storage Storage in dry areas at normal ambient temperatures is recommended. Open containers of unused product should be firmly closed for storage.

TDS-5925 180323

NOTICE: Although the information and recommendations contained in this document (hereinafter "Information") are presented in good faith and believed to be correct at the date of their publication, BAERLOCHER makes no representations or warranties as to the completeness or accuracy of Information.

Information is supplied upon the condition that the persons or entities receiving same will make their own determination as to its suitability for their purposes prior to their use. In no event, will BAERLOCHER be responsible or liable for any loss of profits, lost goodwill, direct, special, indirect, incidental, or consequential damages of any nature whatsoever, including without limitation lost revenue, resulting from the use of or reliance upon Information or the product to which Information refers.

Nothing contained in this disclaimer is to be construed as a recommendation to use any product, process, equipment or formulation in conflict with any patent or intellectual property right, and BAERLOCHER makes no representation or warranty, express or implied, that the use thereof will not infringe any patent or intellectual property rights.

No representations or warranties, either express or implied, of merchantability, fitness for a particular purpose or of any other nature are made hereunder with respect to Information or the product to which Information refers.