

# TEGO® Airex 922

## DESCRIPTION

TEGO® Airex 922 is a silicone-free deaerator that combines strong defoaming with excellent compatibility. Very efficient for solventborne and solvent-free systems.

## KEY BENEFITS

- for solventborne and solvent-free coatings
- ideal for high build epoxy coatings
- highly efficient in low-shear applications

## APPLICATION RECOMMENDATION

### Brush application/roller application



### Airless spraying



### Compressed air spraying



### Flexo/gravure printing



### Dip coating, flow coating, curtain coating



### Flooring




## SUITABILITY

### waterborne




### solventborne



### 2-pack 100%



### radiation-curing



### pigmented coatings



### clear coatings



● not suitable ● partly suitable ● suitable

## TYPICAL APPLICATIONS

- Floor coatings
- High solid industrial coatings
- General industrial coatings
- Others

## TECHNICAL DATA

<b>active matter content</b>	100 %
<b>appearance</b>	colored liquid
<b>chemical description</b>	formulation based on deaerating polymers, silicone-free

## SOLUBILITY

<b>Water</b>	<b>Ethanol</b>
●	●
<b>TPGDA</b>	<b>Acetone</b>
●	●
<b>Butylacetate</b>	<b>Mineral Spirits</b>
●	●

● not soluble ● partly soluble ● soluble

## RECOMMENDED ADDITION LEVEL

As supplied calculated on total formulation: 0.1 - 1.0 %

## PROCESSING INSTRUCTIONS

- Addition as supplied is recommended.
- Predilution in a suitable solvent simplifies dosage and incorporation.

## HANDLING & STORAGE

When stored in an original unopened packaging between -40 and +40 °C, the product has a shelf life of at least 24 months from the date of manufacture.

## MSDS & REGULATORY INFORMATION



This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Resource Efficiency GmbH | Goldschmidtstraße 100, 45127 Essen, Germany | Telefon +49 201 173-2222 Telefax +49 201 173-1939 | [www.coating-additives.com](http://www.coating-additives.com)