

Specifications for  
**SEMTOL<sup>®</sup> 40 White Mineral Oil Tech Grade**

<u>PROPERTIES GUARANTEED</u>	<u>TEST METHOD</u>	<u>LIMITS</u>
Specific Gravity @ 25°C/25°C	ASTM D4052	0.804/0.827
Kinematic Visc. @ 40°C, mm <sup>2</sup> /s	ASTM D445	3.9/5.5
UV Absorbance	21CFR 178.3620(b)	PASS
Color, Saybolt	ASTM D156	30 Min.
Breakdown Time, Minutes	LATM 017	40 Min.
Pour Point, °C	ASTM D97	3 Max
Odor	LATM 092	Tech. Sweet

**TYPICAL PROPERTIES FOR SEMTOL<sup>®</sup> 40 White Mineral Oil Tech Grade**

<u>PROPERTIES</u>	<u>TEST METHOD</u>	<u>TYPICAL VALUE</u>
Saybolt Viscosity @ 100°F, SUS	ASTM D2161	40

The information contained herein is correct to the best of our knowledge. Your attention is directed to the pertinent Safety Data Sheets for the products mentioned herein. All sales are subject to Sonneborn's standard terms and conditions of sale, copies of which are available upon request and which are part of Sonneborn's invoices and/or order acknowledgments. Except as expressly provided in Sonneborn's standard terms and conditions of sale, no warranty, express or implied, including warranty of merchantability or fitness for particular purpose, is made with respect to the products described herein. Nothing contained herein shall constitute permission or recommendation to practice any invention covered by a patent without a license from the owner of the patent.