



### COPRO® SP-462

<b>Description</b>	An all acrylic surfactant stabilized polymer emulsion										
<b>Application</b>	Polymer modifier for hydraulic cement mixtures used for repair, EIFS, decorative overlays, tile grouts and mortars or as a non-rewettable bonding agent.										
<b>Features</b>	<ul style="list-style-type: none"> <li>◆ Excellent clarity, color and UV resistance</li> <li>◆ Low odor</li> <li>◆ Higher solids</li> </ul> <p><u>When added to cementitious systems</u></p> <ul style="list-style-type: none"> <li>◆ Imparts increased flexibility</li> <li>◆ Improved adhesion to substrates such as plywood</li> <li>◆ Excellent weatherability</li> <li>◆ Superior corrosion and water resistance</li> </ul>										
<b>Properties</b>	<table border="0"> <tr> <td>Nonvolatile Content, %</td> <td>52.0 – 54.0</td> </tr> <tr> <td>pH</td> <td>7.0– 8.0</td> </tr> <tr> <td>Viscosity, cps (Brookfield, RV, #3/20rpm/25C°/77°F)</td> <td>50 - 500</td> </tr> <tr> <td>Wt/gal</td> <td>8.8 – 9.0</td> </tr> <tr> <td>Glass transition temperature (Tg), °C</td> <td>+10</td> </tr> </table>	Nonvolatile Content, %	52.0 – 54.0	pH	7.0– 8.0	Viscosity, cps (Brookfield, RV, #3/20rpm/25C°/77°F)	50 - 500	Wt/gal	8.8 – 9.0	Glass transition temperature (Tg), °C	+10
Nonvolatile Content, %	52.0 – 54.0										
pH	7.0– 8.0										
Viscosity, cps (Brookfield, RV, #3/20rpm/25C°/77°F)	50 - 500										
Wt/gal	8.8 – 9.0										
Glass transition temperature (Tg), °C	+10										
<b>Storage</b>	Protect from freezing. Ideal storage temperature 72°F. Stability at 72°F is >180 days.										
<b>Packaging Forms</b>	Available in bulk, totes or drums.										
<b>Important Safety Information</b>	Before using this or any other chemical product, be sure to read and understand the information on the Material Safety Data Sheet and Product Labels. Remain aware of potential hazards and follow all precautionary measures, handling instructions, and disposal considerations outlined in the MSDS and label.										

Rev 6/12

**For help in a Chemical Emergency, call CHEMTREC at 1-800-424-9300**

IMPORTANT: Information, specifications, procedures and recommendations provided ("information") are based on our experience and we believe this to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

**NOTE TO USER:** by ordering/receiving product you accept the H.B. Fuller General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, the total aggregate liability of H.B. Fuller for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses arising out of or in connection with product supply.



## H.B. Fuller

H.B. Fuller North America  
inquiry@hbfuller.com  
**Contact us for details**