

Dynasytan® 9116

Hexadecyltrimethoxysilane

Technical data

Properties and test methods	Value	Unit	Method
Flash point	165/ 329	°C/ °F	DIN 51758
Density (20 °C/ 68 °F)	0.89	g/cm ³	DIN 51757
Viscosity, dynamic (20°C/ 68°F)	7	mPa·s (cSt)	DIN 53015
Boiling point (100 hPa)	180/ 356	°C/ °F	DIN 51751

Registrations

Dynasytan® 9116

EINECS/ELINCS (EU):	Yes
AICS (Australia):	Yes
DSL/NDSL (Canada):	*
PICCS (Philippines):	Yes
TSCA (USA):	Yes
IECS (P.R. China):	Yes
ENCS (Japan):	*
ECL (South Korea):	Yes
REACH (Europe)	Registered
* = information on request	

Dynasytan® 9116 is a monomeric long-chain alkylfunctional silane.

Dynasytan® 9116 is a clear colourless liquid and soluble in common non-polar organic solvents (e.g. petroleum ether, toluene). However its low volatility and viscosity make Dynasytan® 9116 an easy-to-handle additive. During the hydrolysis reaction between water and Dynasytan® 9116 a certain amount of methanol (VOC) is released.

Safety and handling

Before considering the use of Dynasytan® products please read its Safety Data sheet (SDS) thoroughly for safety and toxicological data as well as for information on proper transportation, storage and use. The Safety Data Sheet is available after registration on our website www.dynasytan.com or upon request from your local representative, customer service or from Evonik Resource Efficiency GmbH, Product Safety Department, E-MAIL sds-hu@evonik.com.

Packaging, storage and shelf life

Dynasytan® 9116 is supplied in 180 kg drums and 850 kg containers.

The containers must remain tightly sealed and stored in a cool, well-ventilated place protected against moisture.

Protect from frost (avoid temperatures below 0°C). The product becomes a solid when stored cold (e.g. at -10°C) but can be recovered without deterioration after melting.

In the unopened container Dynasytan® 9116 has a shelf life of min. 12 months from delivery.

Properties and applications

Dynasylan® 9116 silane can be used for the treatment of mineral fillers and pigments or inorganic surfaces in general (e.g. concrete, ATH, MDH). The long-chain alkyl functionality results in unique compound properties (better dispersion, high filler loadings, enhanced mechanical properties, reduced water uptake) when Dynasylan® 9116 treated fillers are incorporated into polymers (e.g. polypropylene).

Key Benefits: Because of its unique structure, Dynasylan® 9116 exhibits superior hydrophobicity on substrates and forms weather- and moisture-resistant bonds to substrates as well.

Use of Dynasylan® 9116 silane results in:

- waterproofing by impregnation when used as a water-repellent
- improvements in toughness in wollastonite-filled polypropylene, allowing the formulation of highly-filled compounds

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

**Europe/Middle-East/Africa/RoW
Evonik Resource Efficiency GmbH**

Business Line Silanes
Rodenbacher Chaussee 4
63457 Hanau-Wolfgang
Germany
PHONE +49 6181 59 13636
FAX +49 6181 59 713915
dynasytan@evonik.com
www.dynasytan.com

**Asia / Pacific
Evonik (SEA) Pte. Ltd.**

Business Line Silanes
3 Internatioanl Business Park
#07-18, Nordic European Centre
Singapore 609927
PHONE +65 6809 6576
FAX +65 6809 6699
dynasytan@evonik.com
www.dynasytan.com

**Asia / Pacific
Evonik Japan Co. Ltd**

Business Line Silanes
12th Floor Monolith Building
2-3-1, Nishi-Shinjuku-ku
Tokyo 163-0912
Japan
PHONE +81 353 23 7446
FAX +81 353 23 7397
dynasytan@evonik.com
www.dynasytan.com

**North America
Evonik Corporation**

Business Line Silanes
299 Jefferson Road
Parsippany, NJ 07054-0677
USA
PHONE (TOLL FREE) +1 800 237 67 45
PHONE +1 973 929 8513
FAX +1 973 929 8503
dynasytan@evonik.com
www.dynasytan.com

**Asia / Pacific
Evonik Specialty
Chemicals (Shanghai) Co. Ltd.**

Business Line Silanes
55, Chungdong Road
Xinzhuang Industry Park
Shanghai 201108
P.R. China
PHONE +86 21 61191-399
FAX +86 21 61191-648
dynasytan@evonik.com
www.dynasytan.com

**Asia / Pacific
Evonik India Pvt. Ltd.**

Business Line Silanes
Krislon House
Saki Vihar Road, Anderi (E)
Mumbai - 400 072
India
PHONE +91 226 7238 809
FAX +91 226 7238 811
dynasytan@evonik.com
www.dynasytan.com

**North America
Silbond Corporation**

9901 Sand Creek Highway
Weston, MI 49289
USA
PHONE +1 517 436 9316
FAX +1 517 436 3148
dynasytan@evonik.com
www.dynasytan.com

**Asia / Pacific
Evonik Korea Ltd.**

Business Line Silanes
94, Galsan 1-dong
Bupyeong-gu
Incheon, 403-081
Korea
PHONE +82 2320 4773
FAX +82 2783 2520
dynasytan@evonik.com
www.dynasytan.com

**Latin America
Evonik Brasil Ltda.**

Business Line Silanes
Alameda Campinas, 579
01404-000 São Paulo-SP
Brazil
PHONE +55 11 3146 4123
FAX +55 11 3146 4148
dynasytan@evonik.com
www.dynasytan.com

**Asia / Pacific
Evonik Taiwan Ltd.**

Business Line Silanes
Artist Construction Bldg.
9F, No. 133
Min Sheng East Road, Sec 3
Taipei, 105 Taiwan, R.O.C.
Taiwan 10596
PHONE +886 227 17 1242
FAX +886 227 17 2106
dynasytan@evonik.com
www.dynasytan.com