

# MOLECULAR Chemical Systems™



## Liquid Polyurethane Elastomer System Technical Data for PM-2000-90

PM-2000-90 is an MDI-based, polyester polyol urethane binder. It is designed for use in systems where medium processing times are required and lipophobic characteristics are desired.

LIQUID Properties	
Property	PM-2000-90
Viscosity @ 77 °F	< 4000 cP
Specific Gravity (@ 77 °F)	1.19
Storage Temperature	60-80 °F
Shelf Life*	6 months
NCO (%)	8.5-9.5

\*Shelf life dependent on storage conditions. Components should be stored in tightly capped containers with nitrogen blanketed head-space. Components should be stored in a temperature controlled environment of approximately 75°F. Avoid extreme temperatures and significant changes in temperature. Always have an MSDS available.

Carpenter Co.  
Chemical Systems Division  
Customer Service 800-444-5132  
[www.carpenter.com](http://www.carpenter.com) 2017-03-14

## Ordering

Molecular Chemical Systems™ are available in bulk (tankwagon), totebin or 55-gallon drums. To place an order or obtain additional information, please call Customer Service at 800-444-5132

## Safety

All sales of products manufactured by Carpenter Co. and described herein are made solely on the condition that our customers comply with applicable health and safety laws, regulations and orders relating to the handling of our products in the workplace.

Before using, please read all product labels and Safety Data Sheet for each product. A general Safety, Health and Toxicity bulletin is also available from Carpenter. All this literature, if presently not on your site, can be obtained from the Customer Service Representative.

Polyurethane products manufactured or produced from this liquid system may represent a serious fire hazard if improperly used or allowed to remain exposed or unprotected. The character and magnitude of any such hazard will depend upon a broad range of factors which are controlled and influenced by the manufacturing and production process, by the mode of application or installation and by the function and usage of the particular product. **Any flammability rating contained in this literature is not intended to reflect hazards presented by this or any other material under actual fire conditions. These ratings are used solely to measure and describe the products response to heat and flame under controlled laboratory conditions.** Each person, firm or corporation engaged in the manufacture, production, application, installation or use of any polyurethane product should carefully determine whether there is a potential fire hazard associated with such product in a specific usage, and utilize all appropriate precautionary and safety measures. In case of an emergency please call Chemtrec at 800-424-9300.

IMPORTANT: The information above is offered for your consideration, investigation and verification. The data is presented in good faith and is believed to be reliable. Carpenter Co., however, makes no representation as to completeness or accuracy. Carpenter Co. makes no warranty expressed or implied with respect to the data contained herein. Carpenter Co. cannot anticipate all conditions under which this data may be used. The conditions of handling, storage, use and disposal of the product are beyond Carpenter Co.'s control. Thus, we expressly disclaim responsibility or liability for any loss, damage or expense arising out of reliance on the information contained herein. You are advised to make your own determination as to safety, suitability and appropriate manner of handling, storage, use and disposal.