


VERSAL RED BR



Characteristic

C. I.	Pigment Red 144
C. I. No.	20735
CAS No.	5280-78-4
Chemical Class	Disazo Cond.

Properties

Oil Absorption [ml/100 g]	78
Density [g/cm ³]	1.5
Bulking Volume [l/kg]	6.3

Fastness

Linseed Oil	5
White Spirite	5
DEHT	5
Xylene	4-5
Acetone	4-5
Butylacetate	4-5
Ethanol	5
Water	5
HCl 2.5%	5
NaOH 2.5%	5
Light - Full Shade	P 7-8
Light - 1/1	7-8
Light - 1/3	7-8
Weather - Full Shade	P 4D
Weather - 1/1	3-4
Weather - 1/3	3-4
Overspray	4-5
Heat Resistance [°C]	P 280
Migration	4-5

P - in Plastics, D - Duller

Application Possibilities

- Printing Inks - Water based ●
- Printing Inks - UV Curing ●



Synthesia, a.s., Semtín 103, 530 02 Pardubice, Czech Republic
 Identification number: 60108916 • VAT: CZ60108916

phone: +420 466 821 111 • fax: +420 466 822 900 • e-mail: synthesia@synthesia.eu
www.synthesia.eu



Paints - Decorative	●	
Paints - Industrial	●	
Paints - Powder Coatings	●	
Plastics - Polyolefines	●	
Plastics - PVC	●	
Plastics - PP Fibers	●	
● main application		○ side application

Other Informations

Shelf Life	48 months
------------	-----------

Testing methods

Density

- determined by ČSN EN ISO 787-10: 1997 (67 0520) in $v \text{ g/cm}^3$

Bulking Volume

- denotes the volume of 1 kg of loosely poured pigment, expressed in litres

Oil Absorbtion

- determined by ČSN EN ISO 787-5: 1997 (67 0520) in ml/100 g pigment

Fastness to Solvents

- colouring of solvent after 24 h at 20 °C according to ISO grey scale is determined; degree 1 denotes the lowest fastness, degree 5 the highest one

Fastness to Reagents

- colouring of reagents after 24 h at 20 °C according to ISO grey scale is determined; degree 1 denotes the lowest fastness, degree 5 the highest one

Light Fastness - Xenotest

- determined by ČSN EN ISO 105-B02: 2000 (80 0147) and evaluated in 1/3 and 1/1 of standard depth and in full shade; determined according to blue scale, by it degree 1 denotes the lowest fastness, degree 8 the highest one

Weathering Fastness - Xenotest

- determined by ČSN EN ISO 105-B04: 1998 (80 0171) and evaluated in 1/3 and 1/1 of standard depth and in full shade; determined according to grey scale, by it degree 1 denotes the lowest fastness, degree 5 the highest one

Overspray Fastness

- assessment of bleeding into a white nitrocellulose combination lacquer for 60 min. at 70 °C against ISO grey scale; by it degree 1 denotes the lowest fastness, degree 5 the highest one

Heat Resistance

- the values quoted indicate up to what temperature the pigments do not significantly alter; these are guide values which can be influenced by the binder used and the period of exposure to high temperature

Migration Fastness

- assessment of bleeding into a white polyvinylchloride sheet for 24 h at 70 °C against ISO grey scale; by it degree 1 denotes the lowest fastness, degree 5 the highest one; no data means that the pigment is not recommended for dyeing of PVC

Fastness to plasticizers

- colouring of plasticizer (diethylhexylterephthalate) after 24 h at 20 °C according to ISO grey scale is determined; degree 1 denotes the lowest fastness, degree 5 the highest one