

## Protectosil® WS 610

Protectosil® WS 610 is a high performance water repellent emulsion for masonry

### Technical Data

Properties and test methods	Value	Unit	Method
Density (20 °C)	approx. 1,017	g/cm <sup>3</sup>	DIN 51757
Appearance	white liquid	-	-
Flash point	> 95	°C	EN 22719
Viscosity (20 °C)	approx. 12	mPa's	DIN 53015
pH-value (20 °C)	6,5 - 8,5	-	-
Active ingredient	50	%	-

### Registration

#### Protectosil® WS 610

EINECS/ELINCS (EU):	Yes
AICS (Australia):	No
DSL/NDSL (Canada):	*
PICCS (Philippines):	Yes
TSCA (USA):	Yes
IECSC (P.R. China):	*
ENCS (Japan):	No
ECL (South Korea):	Yes
* = Information upon request	

Protectosil® WS 610 is an organofunctional siloxane based waterborne emulsion with almost no volatile organic components (VOC). Protectosil® WS 610 is used for water proofing of mineral building materials.

The main application is facade impregnation creating a water beading effect at the surface. Protectosil® WS 610 reduces the ingress of water and waterborne contaminants into the substrate and thereby prevents premature deterioration. Protectosil® WS 610 chemically bonds with silica to form a permanent attachment of water repellent molecules while also providing an excellent beading effect on the surface. Protectosil® WS 610 is supplied as a 50 % water-borne emulsion. It is mainly used to manufacture formulations with lower concentration of active ingredient in water.

### Safety and Handling

Before considering the use of Protectosil® products please read its Safety Data sheet (SDS) thoroughly for safety and toxicological data as well as for information on proper transportation, storage and use. The Safety Data Sheet is available after registration on our website [www.protectosil.com](http://www.protectosil.com) or upon request from your local representative, customer service or from Evonik Resource Efficiency GmbH, Product Safety Department, E-MAIL [sds-hu@evonik.com](mailto:sds-hu@evonik.com).

### Packaging and Storage

Protectosil® WS 610 has a shelf life of one year if stored in originally sealed containers.

Protectosil® WS 610 should be stored between 3 °C and 40 °C. Protectosil® WS 610 is supplied in 25 l PE canisters and 200 l plastic lined steel drums and 1.000 l bulk container.

## Properties and Use

As hydrophobic agent for mineral building materials especially facades with high porosity e.g.

- mineral rendering
- sand-lime brickwork
- hard-baked brickwork
- roofing tiles
- concrete surfaces

### Product characteristics after application

- water vapor permeable, colorless
- waterproofing with surface beading
- no formation of a sticky silicone film
- effective on micro cracks up to 0.3 mm
- high reduction of water absorption
- high water repellent effect and good penetration in absorbent mineral building materials

### Instructions for use:

Substrates should be dry and clean prior to application to ensure deep penetration of the water repellent. Avoid application during strong wind or rain. It is not possible to apply Protectosil® WS 610 on a painted surface, as the mineral groups of the substrate must be accessible for the product to create a strong bonding, which is essential for good long-term performance.

Due to its high water content, the impregnating solution is sensitive to frost and cannot be applied at sub-freezing temperatures. Outside temperature and surfaces temperature should be above 5 °C. Protectosil® WS 610 should be applied using low pressure pumping equipment with a wet fan type spray nozzle. Do not apply to a wet or damp substrate.

On vertical surfaces apply the Protectosil® WS 610 in a flooding application, so the material runs down 15–20 cm (6 to 8 inches) below the spray pattern. On horizontal surfaces the liquid material should pond on the surface at least 5 seconds before being absorbed. A test patch should be applied to the substrate to verify coverage rate and application conditions. Protect glass, metal, plastic, and other nonporous substrates from overspray.

Protectosil® WS 610 will not etch glass, but will leave a residue on nonporous surfaces. Most liquid delivery devices are suitable (e.g. airless spray guns). The material should not be atomized or applied with a brush. This can cause de-emulsification of the product. Temperature and type of substrate are factors, which will determine how fast the water repellent effect develops. The application must be carried out in sections, continuously and without break to avoid overlapping. The recommended concentration is 10% of active ingredient in water. This corresponds to a dilution with water (preferable demineralized water) of 1:4. Protectosil® WS 610 is not recommended to be applied undiluted. Minimum dilution rate should be 1:1. The quantity and concentration to be applied depend on the absorbency of the substrate to be treated and the desired depth of penetration. Porous substrates may require well over 350 ml/m<sup>2</sup> of the water repellent. The exact quantity and the optimum concentration to be applied should be determined by a trial application. For red brick we recommend a consumption rate of at least 240 ml/m<sup>2</sup>.

Non-absorbent substrates cannot be treated, as drying may cause the formation of a sticky film. This film will harden over time and can be removed using chemical strippers, spirit of soap or solvents. Plants are to be protected against contact with the water repellent agent. Protectosil® WS 610 reacts with the boundary surfaces in pores and capillaries of the mineral surface and forms an invisible, water-repellent boundary surface compound. As possible previous treatments of the substrate might be unknown, it is always advisable to carry out a test to make sure that there are no undesirable accompanying effects.

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

**Europe / Middle-East / Africa / Row**

**Evonik Resource Efficiency GmbH**

Business Line Silanes  
Rodenbacher Chaussee 4  
63457 Hanau-Wolfgang  
Germany  
PHONE +49 6181 59 13636  
FAX +49 6181 59 713 915  
protectosil@evonik.com  
www.protectosil.com

**Asia / Pacific**

**Evonik (SEA) Pte. Ltd.**

Business Line Silanes  
3 Internatioanl Business Park  
#07-18, Nordic European Centre  
Singapore 609927  
PHONE +65 6809 6899  
FAX +65 6809 6699  
protectosil@evonik.com  
www.protectosil.com

**Asia / Pacific**

**Evonik Taiwan Ltd.**

Business Line Silanes  
Artist Construction Bldg  
9F, No. 133  
Min Sheng East Road, Sec 3  
Taipei, 105 Taiwan, R.O.C.  
Taiwan 10596  
PHONE +886 227 17 1242  
FAX +886 227 17 2106  
protectosil@evonik.com  
www.protectosil.com

**North America**

**Evonik Corporation**

Business Line Silanes  
299 Jefferson Road  
Parsippany, NJ 07054-0677  
USA  
PHONE (TOLL FREE) +1 800 828 0919  
FAX +1 973 929 8503  
protectosil@evonik.com  
www.protectosil.com

**Asia / Pacific**

**Evonik (Shanghai) Co. Ltd.**

Business Line Silanes  
55, Chungdong Road  
Shanghai 201108  
P.R. China  
PHONE +86 21 6119 1660  
FAX +86 21 6119 1075  
protectosil@evonik.com  
www.protectosil.com

**Asia / Pacific**

**Evonik Japan Co. Ltd**

Business Line Silanes  
12th Floor Monolith Building  
2-3-1, Nishi-Shinjuku-ku  
Tokyo 163-0912  
Japan  
PHONE +81 353 23 7446  
FAX +81 353 23 7397  
protectosil@evonik.com  
www.protectosil.com

**Latin America**

**Evonik Brasil Ltda.**

Business Line Silanes  
Alameda Campinas, 579  
01404-000 São Paulo-SP  
Brazil  
PHONE +55 11 3146 4123  
FAX +55 11 3146 4148  
protectosil@evonik.com  
www.protectosil.com

**Asia / Pacific**

**Evonik Korea Ltd.**

Business Line Silanes  
94, Galsan 1-dong  
Bupyeong-gu  
Incheon, 403-081, Korea  
PHONE +82 2320 4778  
FAX +82 2783 2520  
protectosil@evonik.com  
www.protectosil.com

**Asia / Pacific**

**Evonik India Pvt. Ltd.**

Business Line Silanes  
Krislon House  
Saki Vihar Road, Anderi (E)  
Mumbai - 400 072  
India  
PHONE +91 226 7238 809  
FAX +91 226 7238 811  
protectosil@evonik.com  
www.protectosil.com