

# PEBAX®

## 6333 SP 01

Polyether block amide **Pebax® 6333 SP 01 resin** is a thermoplastic elastomer made of flexible polyether and rigid polyamide. This SP grade has been developed to be heat and UV resistant.

### MAIN CHARACTERISTICS

PROPERTIES	DRY / COND	UNIT	TEST STANDARD
<b>RHEOLOGICAL PROPERTIES</b>			
Molding Shrinkage, parallel	1.2 / *	%	ISO 294-4, 2577
Molding Shrinkage, normal	1.4 / *	%	ISO 294-4, 2577
<b>MECHANICAL PROPERTIES</b>			
Tensile Modulus	307 / 285	MPa	ISO 527-1/-2
Yield stress	19 / 18	MPa	ISO 527-1/-2
Yield strain	22 / 22	%	ISO 527-1/-2
Nominal Strain at Break	>50 / >50	%	ISO 527-1/-2
Stress at 10% Elongation	14 / *	MPa	ISO 527-1/-2
Stress at 100% Elongation	17 / *	MPa	ISO 527-1/-2
Strain at Break TPE	>300 / *	%	ISO 527-1/-2
Stress at Break TPE	53 / *	MPa	ISO 527-1/-2
Compression Set at 23 °C, 24h	47 / *	%	ISO 815
Tear Strength	127 / *	kN/m	ISO 34-1
Abrasion Resistance	55 / *	mm <sup>3</sup>	ISO 4649
Shore D Hardness	58 / *	-	ISO 868
Charpy Impact Strength, +23°C	No Break / No Break	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy Impact Strength, -30°C	No Break / No Break	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy Notched Impact Strength, +23°C	No Break / No Break	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy Notched Impact Strength, -30°C	- / 20	kJ/m <sup>2</sup>	ISO 179/1eA
<b>THERMAL PROPERTIES</b>			
Melting Temperature, 10°C/min	169 / *	°C	ISO 11357-1/-3
Temp. of Deflection Under Load, 0.45 MPa	90 / *	°C	ISO 75-1/-2
Vicat Softening Temperature, 50°C/h 50N	157 / *	°C	ISO 306
Coeff. of Linear Thermal Expansion, parallel	140 / *	E-6/K	ISO 11359-1/-2
Oxygen Index	20 / *	%	ISO 4589-1/-2
<b>ELECTRICAL PROPERTIES</b>			
Relative Permittivity, 100Hz	9 / -	-	IEC 60250
Relative Permittivity, 1MHz	4 / -	-	IEC 60250
Dissipation Factor, 100Hz	1440 / -	E-4	IEC 60250

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

# PEBAX®

## 6333 SP 01

<b>Dissipation Factor, 1MHz</b>	757 / -	E-4	IEC 60250
<b>Volume Resistivity</b>	9E11 / -	Ohm*m	IEC 60093
<b>Surface Resistivity</b>	* / 1E13	Ohm	IEC 60093
<b>Dielectric (Electric) Strength</b>	42.5 / -	kV/mm	IEC 60243-1
<b>Comparative Tracking Index</b>	* / 600	-	IEC 60112
<b>OTHER PROPERTIES</b>			
<b>Water Absorption</b>	1.1 / *	%	Sim. to ISO 62
<b>Humidity Absorption</b>	0.7 / *	%	Sim. to ISO 62
<b>Density</b>	1010 / 1010	kg/m <sup>3</sup>	ISO 1183
<b>Spec. heat capacity of melt</b>	2800	J/(kg K)	-
<b>Thermal conductivity of melt</b>	0.18	W/(m K)	-
<b>Density of melt</b>	830	kg/m <sup>3</sup>	-

**MAIN APPLICATIONS:** • Athletic foot wear components • Ski boots

### PACKAGING:


This grade is delivered dried in sealed packaging (20 or 25 kg bags) ready to be processed.

### SHELF LIFE:


Two years from the delivery. For any use above this limit, please refer to our technical services.

### DIAGRAMS


#### VISCOSITY-SHEAR RATE




#### SHEARSTRESS-SHEAR RATE




#### DYNAMIC SHEAR MODULUS-TEMPERATURE




#### STRESS-STRAIN




### SECANT MODULUS-STRAIN




### STRESS-STRAIN (ISOCHRONOUS) 23 °C




### STRESS-STRAIN (ISOCHRONOUS) 40 °C




### CREEP MODULUS-TIME 40 °C




### STRESS-STRAIN (ISOCHRONOUS) 60°C




### CREEP MODULUS-TIME 60°C




### STRESS-STRAIN (ISOCHRONOUS) 80°C



### CREEP MODULUS-TIME 80°C



### SPECIFIC VOLUME-TEMPERATURE (PVT)



#### Processing conditions:

- Typical melt temperature (Min / Recommended / Max) : 230°C / 260°C / 290°C.
- Typical mold temperature : 25 – 60°C.
- Drying time and temperature (only necessary for bags opened for more than two hours) : 4-6 hours at 65-75°C.

#### Processing conditions:

- Typical melt temperature (Min / Recommended / Max) : 210°C / 225°C / 240°C.
- Drying time and temperature (only necessary for bags opened for more than two hours) : 4-6 hours at 65-75°C.

### PROCESSING

Injection Molding, Film Extrusion, Profile Extrusion, Other Extrusion, Transfer Molding, Casting, Thermoforming

### DELIVERY FORM

Pellets

### SPECIAL CHARACTERISTICS

Heat Stabilized, Light Stabilized

### REGIONAL AVAILABILITY

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

Pebax® is a registered trademark of Arkema  
© 2022 Arkema Inc. All rights reserved.

# ARKEMA