

Protectosil® WS 602

Aqueous emulsion for the water repellent treatment of mineral porous materials.

Technical Data

Properties and test methods	Value	Unit	Method
Density (20 °C)	approx. 1,017	g/cm ³	DIN 51757
Appearance	white liquid	-	-
Flash point	> 90	°C	EN 22719
Viscosity (20 °C)	approx. 20	mPa.s	DIN 53015
Active ingredient	50	%	-
pH (20°C)	6,5 - 8,5	-	-

Registration

Protectosil® WS 602

EINECS/ELINCS (EU):	Yes
AICS (Australia):	No
DSL/NDSL (Canada):	*
PICCS (Philippines):	Yes
TSCA (USA):	Yes
IECSC (P.R. China):	*
ENCS (Japan):	Yes
ECL (South Korea):	Yes
TCSI (Taiwan)	Yes
*= Information upon request	

Aqueous emulsion for the water repellent treatment of mineral porous materials, especially facades. Essentially VOC free.

Safety and Handling

Before considering the use of Protectosil® products please read its Safety Data sheet (SDS) thoroughly for safety and toxicological data as well as for information on proper transportation, storage and use. The Safety Data Sheet is available on our website www.protectosil.com or upon request from your local representative, customer service or from Evonik Operations GmbH, Product Safety Department, E-MAIL sds-hu@evonik.com.

Packaging and Storage

Protectosil® WS 602 is supplied in 25 l PE-containers, 200 l steel drums with PE-inliner and 1.000 l containers. Protectosil® WS 602 is not frost resistant and should not be stored at temperatures below 3 °C. Only demineralized water should be used for dilutions. Protectosil® WS 602 should be stored at temperatures between 3 °C and 40 °C. Protectosil® WS 602 has a shelf life of 12 months if properly stored in originally sealed containers.

Properties and Use

Protectosil® WS 602

- is suited for the water-repellent impregnation of porous mineral substrates
- is very efficient on mineral renders, sand-lime brickwork, hard-baked brickwork, roofing tiles
- shows very good penetration on absorbent mineral materials
- gives water vapor permeable, colorless protection
- reduces significantly the uptake of water
- can be diluted with water

We recommend using a minimum concentration of 10% of the active ingredient in water. This corresponds to a dilution with water (preferable demineralized water) of 1:4. Protectosil® WS 602 is not recommended to be applied undiluted. Minimum dilution rate should be 1:1.

The concentration to be used and the exact amount to be applied are depending on the absorbance of the substrate.

The substrates to be treated should be dry and clean. Acceptable surface cleaning methods include sandblasting and water blasting.

During application outside temperatures and surface temperatures should be between 5 °C and 40 °

C. Protectosil® WS 602 should not be applied during strong wind or rain.

Protectosil® WS 602 should be applied by wet-on-wet flow coating to the saturation point. The solution should be applied in 2 - 3 coats without drying between the coats. On vertical surfaces the solution should run down in the form of a clearly visible descending wet curtain. This is achieved by allowing the solution to flow against the surface of the building material without pressure. Most liquid delivery devices e.g. airless pumping equipment are suitable. The material should not be atomized or applied with a brush.

The water repellent effect of Protectosil® WS 602 can develop within minutes or require up to several days depending on the substrate and weather conditions. Therefore, the impregnation should be applied continuously and without a break to avoid overlapping.

Non-absorbent substrates such as window frames, window sills, plastic fittings, window glass, etc., should be covered before application. Surfaces which accidentally come into contact with Protectosil® WS 602 can be cleaned with alcohol (spirit) or aqueous soap solution. Cleaning should be carried out as quickly as possible (within a few hours), otherwise formation of a silicone resin film can make cleaning more difficult. Silicone resin films are best removed using ethanol (or spirit). Plant life should be protected from overspray.

Protectosil® WS 602 reacts with the interfaces in pores and capillaries of the mineral surface and forms invisible, waterrepellent interfacial compounds. To determine the exact amount to be applied and to check whether previous or following treatments are compatible with the Protectosil® WS 602 treatment it is recommended to do a small test patch first.

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

Europe / Middle-East / Africa

Evonik Operations GmbH

Silanes Business Line
Rodenbacher Chaussee 4
63457 Hanau-Wolfgang
Germany
FAX +49 6181 59 713 915
protectosil@evonik.com
www.protectosil.com

Asia / Pacific

Evonik (SEA) Pte. Ltd.

Silanes Business Line
3 Internatioanl Business Park
#07-18, Nordic European Centre
Singapore 609927
PHONE +65 6809 6906
FAX +65 6809 6699
protectosil@evonik.com
www.protectosil.com

Asia / Pacific

Evonik Taiwan Ltd.

Silanes Business Line
Artist Construction Bldg
9F, No. 133
Min Sheng East Road, Sec 3
Taipei, 105 Taiwan, R.O.C.
Taiwan 10596
PHONE +886 227 17 1242 #247
FAX +886 227 17 2106
protectosil@evonik.com
www.protectosil.com

North America

Evonik Corporation

Silanes Business Line
299 Jefferson Road
Parsippany, NJ 07054
USA
PHONE (TOLL FREE) +1 800 828 0919
protectosil@evonik.com
www.protectosil.com

Asia / Pacific

Evonik (Shanghai) Co. Ltd.

Silanes Business Line
55, Chungdong Road
Shanghai 201108
P.R. China
PHONE +86 21 6119 1660
FAX +86 21 6119 1075
protectosil@evonik.com
www.protectosil.com

Asia / Pacific

Evonik Japan Co. Ltd

Silanes Business Line
12th Floor Monolith Building
2-3-1, Nishi-Shinjuku-ku
Tokyo 163-0912
Japan
PHONE +81 353 23 7446
FAX +81 353 23 7397
protectosil@evonik.com
www.protectosil.com

Region Central and South America

Evonik Brasil Ltda.

Silanes Business Line
Rua Arquiteto Olavo Redig de Campos, 105
Torre A - 04711-904 São Paulo- SP
Brazil
PHONE +55 11 3146 9627
protectosil@evonik.com
www.protectosil.com

Asia / Pacific

Evonik Korea Ltd.

Silanes Business Line
3F (Nongshim Sungmookwan B/D)
112 Yeouidaebang-Ro
Dongjak-Gu
Seoul, 07057
Korea
PHONE +82 2320 4778
FAX +82 2783 2520
protectosil@evonik.com
www.protectosil.com

Asia / Pacific

Evonik India Pvt. Ltd.

Silanes Business Line
Krislon House
Saki Vihar Road, Anderi (E)
Mumbai - 400 072
India
PHONE +91 226 7238 809
FAX +91 226 7238 811
protectosil@evonik.com
www.protectosil.com