

# Technical Data Sheet

## POLYGLYKOL B 11/70

Base oil component for industrial applications

<b>Composition</b>	Polyalkylene glycol (ethylene oxide/propylene oxide random copolymer mono butyl ether) $\text{CH}_3\text{CH}_2\text{CH}_2\text{CH}_2(\text{OCH}_2\text{CH}_2)_n(\text{OCH}_2\text{CHCH}_3)_m$ OH n:m = 1:1
<b>Product properties <sup>1</sup></b>	
<b>Appearance (20°C)</b>	Clear viscous liquid
<b>Color index [APHA] EN 1557</b>	Max. 100
<b>Refractive index (20°C) DIN 51432</b>	Approx. 1.457 -1.458
<b>Molecular weight</b>	Approx. 1600 g/mol
<b>Water content DIN 51777</b>	Max. 0.5 %
<b>pH value (10% w/w in water) DIN EN 1262</b>	Approx. 5.0 – 7.0
<b>Contact angle V2A steel (5% in aq.*)</b>	Approx. 50.3 °
<b>Surface tension (5% in aq. **)</b>	Approx. 43.2 mN/m
<b>Density (20°C) DIN 51757</b>	Approx. 1.040 – 1.050 g/cm <sup>3</sup>
<b>Viscosity (40°C) DIN 51562</b>	Approx. 100 mm <sup>2</sup> /s
<b>Viscosity (100°C) DIN 51562</b>	Approx. 20 mm <sup>2</sup> /s
<b>Viscosity index ASTM D2270</b>	Approx. 225
<b>Cloud point (1% in aq.)</b>	Approx. 53°C
<b>Cloud point (5g in 25g 25% BDG)</b>	Approx. 50°C
<b>Pour point ISO 3016</b>	Approx. -45°C
<b>Flash point DIN 51794</b>	Approx. 250°C
<b>Ignition temperature DIN 51794</b>	Approx. 360°C
<b>Four ball test DIN 51350/3B (60min. / 300N)</b>	Approx. 0.62 mm
<b>Seizure / welding load</b>	Approx. 1400 / 1800 N
<b>FZG load stage DIN 51354</b>	Approx. 11

### Profile

<sup>1</sup> These characteristics are for guidance only and not to be taken as product specifications. The tolerances are given in the product specification sheet. For further product properties, specifications, safety and ecological data, please refer to the MSDS.

\*) Contact angle of water on V2A steel: 64°

\*\*) Surface tension of water: 71.6 mN/m

## Product properties

Polyglykol B 11/70 is a clear, neutral viscous liquid at room temperature. It is soluble in water and polar organic solvents like acetone or methanol at room temperature. It is insoluble in pure hydrocarbons. Polyglykol B 11/70 displays a very low solidification point of  $-45^{\circ}\text{C}$  and no evaporation loss, even at temperatures as high as  $100^{\circ}\text{C}$ . The hygroscopy of polyglycols increase with the EO ratio in the polymer.

## Application

Based on their physical and chemical characteristics B 11-type polyglycols are used for a wide variety of applications.

Fields of industrial application:

- Low viscous base oil component for high performance lubricants with low friction coefficients, excellent wear properties and good thermal stability
- Water soluble, lubricating component of metalworking fluids, e.g. fully synthetics
- Component of auxiliaries for leather and textile processing
- Defoamer for food and non-food applications
- Reactive alcohol component in chemical reactions
- Solvent and humectants for dyes and inks
- Heat transfer medium

To increase the stability against thermo oxidative degradation Lubricant Additive 1655 can be used.

## Sustainability

Polyglykol B 11/70 is readily biodegradable. It is included in the LuSC-list (Lubricant Substance Classification list) and meets the EU Ecolabel criteria for lubricants (Commission decision 2018 / 1702 / EU).

## Safety

Please see Material Safety Data Sheet before handling the material.

## Storage behaviour

CLARIANT INTERNATIONAL LTD

Rothausstrasse 61  
4132 MuttENZ  
Switzerland

BUSINESS UNIT INDUSTRIAL &  
CONSUMER SPECIALTIES

[www.ics.clariant.com](http://www.ics.clariant.com)  
[www.clariant.com](http://www.clariant.com)

When stored in a cold, dry place in a closed container Polyglykol B 11/70 can be kept for at least two years.

CLARIANT INTERNATIONAL LTD

Rothausstrasse 61  
4132 Muttenz  
Switzerland

BUSINESS UNIT INDUSTRIAL &  
CONSUMER SPECIALTIES

[www.ics.clariant.com](http://www.ics.clariant.com)  
[www.clariant.com](http://www.clariant.com)

This information corresponds to the present state of our knowledge and is intended as a general description of our products and their possible applications. Clariant makes no warranties, express or implied, as to the information's accuracy, adequacy, sufficiency or freedom from defect and assumes no liability in connection with any use of this information. Any user of this product is responsible for determining the suitability of Clariant's products for its particular application.\* Nothing included in this information waives any of Clariant's General Terms and Conditions of Sale, which control unless it agrees otherwise in writing. Any existing intellectual/industrial property rights must be observed. Due to possible changes in our products and applicable national and international regulations and laws, the status of our products could change. Material Safety Data Sheets providing safety precautions, that should be observed when handling or storing Clariant products, are available upon request and are provided in compliance with applicable law. You should obtain and review the applicable Material Safety Data Sheet information before handling any of these products. For additional information, please contact Clariant.

**\* For sales to customers located within the United States and Canada the following applies in addition:**

NO EXPRESS OR IMPLIED WARRANTY IS MADE OF THE MERCHANTABILITY, SUITABILITY, FITNESS FOR A PARTICULAR PURPOSE OR OTHERWISE OF ANY PRODUCT OR SERVICE.

© 2021 Clariant International Ltd,  
Rothausstrasse 61, 4132 Muttenz, Switzerland

