

Dynasytan® F 8263

Fluoroalkylsilane formulation, ready-for-use in i-propanol

Technical data

Properties and test methods	Value	Unit	Method
Viscosity (20 °C)	2	mPa.s	DIN 53015
Flash point	21	°C	DIN EN ISO 13736
Density (20 °C)	0.80	g/cm ³	DIN 51757

Registrations

Dynasytan® F 8263

EINECS/ELINCS (EU):	Yes
AICS (Australia):	Yes
DSL/NDSL (Canada):	*
PICCS (Philippines):	No
TSCA (USA):	Yes; for professional or industrial use only. It is
a violation of federal law for this product to be	distributed to or used by consumers (40CFR721.3)
IECS (P.R. China):	Yes
ENCS (Japan):	*
ECL (South Korea):	Yes
* = available on request	

Dynasytan® F 8263 acts as a surface modifier on oxidic, carboxy- and hydroxyfunctional substrates (e.g. glass, ceramic).

Dynasytan® F 8263 is a colorless liquid. It can be diluted in alcohols and various other organic solvents, e.g. n-hexane, xylol, acetone or ethyl acetate.

Safety and handling

Before considering the use of Dynasytan® products please read its Safety Data Sheet (SDS) thoroughly for safety and toxicological data as well as for information on proper transportation, storage and use. The Safety Data Sheet is available after registration on our website www.dynasytan.com or upon request from your local representative, customer service or from Evonik Resource Efficiency GmbH, Product Safety Department, E-MAIL sds-hu@evonik.com.

Packaging, storage and shelf life

Dynasytan® F 8263 is supplied in drums and containers containing 20 kg, 150 kg and 750 kg.

In the original closed container, the shelf life of Dynasytan® F 8263 is min. 6 months from delivery.

Properties and applications

Dynasylan® F 8263 can be used highly beneficial in a vast variety of commercial applications:

- Anti-soiling, water-repellent, UV-resistant coating of float glass (constructive glazing)
- Treatment of automotive glass (wiperless windshield)
- Coatings on polymers
- Anti-soiling coatings of ceramic and enamel

Reactivity

Dynasylan® F 8263 is a bifunctional organic compound: The silicon functional alkoxy groups can react with oxides, hydroxy and carboxy functions on the surface of a substrate. They hydrolyze with water and can establish a permanent chemical bond by elimination of ethanol/water. The fluoroalkylfunctional group provides a low energy surface.

Excellent hydrophobic and oleophobic surface properties can also be achieved by treatment with commercial fluorocarbon surfactants and resins. However, besides providing these properties Dynasylan® F 8263 can bond chemically to the surface thus creating a Si-O-substrate - bond. Subsequently, horizontal crosslinking takes place, predominantly upon evaporation of the solvent. Finally 2- and 3-dimensional networks are formed.

Dynasylan® F 8263 is a ready-for-use product and can be directly applied on a surface. Subsequently, stable coatings with a thickness of some nanometers are formed.

Through a special catalyst system which is part of the formulation, Dynasylan® F 8263 can establish coatings on several at least slightly polar polymers, like polyamide, PMMA and polycarbonate.

Processing

Surfaces need to be absolutely clean and degreased before treatment!

For a primer treatment (e.g. on glass) Dynasylan® F 8263 can be applied by polishing with a paper pad (or soft cotton cloth, sponge etc.), which had been previously soaked with the formulation. It is important to maintain a homogeneous liquid film on the whole surface to be treated. A contact time of at least 2 minutes with the surface is required. If the liquid starts to evaporate, thus leaving some exposed domains, additional Dynasylan® F 8263 has to be added. Proper conditions have to be evaluated in detail according to the specific kind and reactivity of the surface.

Hydro-/oleophobicity almost immediately appears upon treatment (autophobic effect) and the phenomenon will increase further over a couple of minutes. Complete crosslinking will take hours to several days at room temperature because the process will be continued long after the treated area has become visibly dry. However, a nearly complete crosslinking can be accelerated by heating the workpiece at 80–150 °C for several hours in a drying oven. Thereafter, eventually formed silicon spots on the surface can be removed by polishing with a smooth pad which had been previously impregnated with a few drops of ethanol.

Polishing aids (sponge, pads) have to be clean and dry before use and reuse is only recommended upon careful cleaning. The formed polysiloxane film is completely invisible and will not lead to any optical impairment on the substrate.

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

Europe/Middle-East/Africa/RoW
Evonik Resource Efficiency GmbH

Business Line Silanes
Rodenbacher Chaussee 4
63457 Hanau-Wolfgang
Germany
PHONE +49 6181 59 13636
FAX +49 6181 59 713915
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific
Evonik (SEA) Pte. Ltd.

Business Line Silanes
3 Internatioanl Business Park
#07-18, Nordic European Centre
Singapore 609927
PHONE +65 6809 6576
FAX +65 6809 6699
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific
Evonik Japan Co. Ltd

Business Line Silanes
12th Floor Monolith Building
2-3-1, Nishi-Shinjuku-ku
Tokyo 163-0912
Japan
PHONE +81 353 23 7446
FAX +81 353 23 7397
dynasytan@evonik.com
www.dynasytan.com

North America
Evonik Corporation

Business Line Silanes
299 Jefferson Road
Parsippany, NJ 07054-0677
USA
PHONE (TOLL FREE) +1 800 237 67 45
PHONE +1 973 929 8513
FAX +1 973 929 8503
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific
Evonik Specialty
Chemicals (Shanghai) Co. Ltd.

Business Line Silanes
55, Chungdong Road
Xinzhuang Industry Park
Shanghai 201108
P.R. China
PHONE +86 21 61191-399
FAX +86 21 61191-648
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific
Evonik India Pvt. Ltd.

Business Line Silanes
Krislon House
Saki Vihar Road, Anderi (E)
Mumbai - 400 072
India
PHONE +91 226 7238 809
FAX +91 226 7238 811
dynasytan@evonik.com
www.dynasytan.com

North America
Silbond Corporation

9901 Sand Creek Highway
Weston, MI 49289
USA
PHONE +1 517 436 9316
FAX +1 517 436 3148
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific
Evonik Korea Ltd.

Business Line Silanes
94, Galsan 1-dong
Bupyeong-gu
Incheon, 403-081
Korea
PHONE +82 2320 4773
FAX +82 2783 2520
dynasytan@evonik.com
www.dynasytan.com

Latin America
Evonik Brasil Ltda.

Business Line Silanes
Alameda Campinas, 579
01404-000 São Paulo-SP
Brazil
PHONE +55 11 3146 4123
FAX +55 11 3146 4148
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific
Evonik Taiwan Ltd.

Business Line Silanes
Artist Construction Bldg.
9F, No. 133
Min Sheng East Road, Sec 3
Taipei, 105 Taiwan, R.O.C.
Taiwan 10596
PHONE +886 227 17 1242
FAX +886 227 17 2106
dynasytan@evonik.com
www.dynasytan.com