


 High performance **KOLon's REZ(s)**in C5 Resins

## Technical Data Sheet : T-1100

### 1.Description

**HIKOREZ® T-1100** is pale yellow thermoplastic resin obtained from polymerizing unsaturated aliphatic olefins and diolefins derived from the process of thermal cracking of naphtha. The major usages are tackifier for solvent based pressure sensitive adhesive(SBPSA), hot melt based pressure sensitive adhesive(HMPSA) and hot melt adhesive(HMA).

### 2.Product specifications

• Softening Point (Ring & Ball, °C)	94-102	ASTM E-28
• Color (Molten Resin, Ga.#)	Max 6	ASTM D-1544

### 3.Typical properties

• Specific Gravity (20/20°C)	1.01	ASTM D-71
• Softening Point (Ring & Ball, °C)	100	ASTM E-28
• Color (Molten Resin, Ga.#)	4	ASTM D-1544
• Heat Stability (@200°C, 3hrs, Ga.#)	6	ASTM D-1544
• Acid Value (KOH mg/g)	0.13	ASTM D-1639
• Melt Viscosity BRF, @140°C, cps	6,000	ASTM D-3236
BRF, @200°C, cps	150	
• Molecular Weight (GPC, Mw)	2,100	G.P.C

*Kolon Industries and its marketing affiliates shall not be responsible for the use of this information, or of any product, method or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.*

## 4.Packaging & Storage

### •Packaging

Available in multi-ply paper bags of 25kg net weight.

### • Storage

Pelletized forms of resins may block or lump.It is recommended,

- to store inside and keep cool condition  
(30°C max / resin with softening point below 100°C - 25°C max)
- not stacking pallets
- to avoid sunlight

Especially, low softening point resins(below 100 °C) has a higher possibility of blocking due to the nature of product. Therefore, we strongly recommend that keep storing in more strict conditions.

## 5.Shelf life

The shelf life can be affected by storage and handling conditions. When products are stored in the original unopened container in an enclosed area and protected from contamination,moisture and extreme temperatures, the shelf life of HIKOREZ® is **1 year** from the date of manufacture.

Shelf life is a guide not an absolute value, and KOLON doesn't control end uses and storage conditions at customers. Therefore, the product should be reanalyzed for properties at the end of its shelf life to see if it meets specification for use.

## 6.Regulatory status

**HIKOREZ® T-1100** is in compliance with the requirements of the U.S FDA for following sections.

<u>175.105</u>	<u>Adhesives</u>
<u>175.125</u>	<u>Pressure sensitive adhesives</u>
<u>175.300</u>	<u>Resinous and polymeric coatings</u>
<u>175.320</u>	<u>Resinous and polymeric coatings for poly olefin films</u>
<u>176.170</u>	<u>Components of paper and paperboard in contact with aqueous and fatty foods.</u>
<u>176.180</u>	<u>Components of paper and paperboard in contact with dry food</u>
<u>177.1210</u>	<u>Closures with sealing gaskets for food containers</u>
<u>177.2600</u>	<u>Rubber articles intended for repeated use</u>

### **Contact**

- Head Office : 4th FL, One&Only tower, 110, Magokdong-ro, Gangseo-gu, Seoul, Republic of Korea (07793)  
TEL) 82-2-3677-6156                      FAX) 82-2-3677-5562
- Ulsan Plant : 33, Sapyeong-ro, Nam-gu, Ulsan, Republic of Korea (44786)  
TEL) 82-52-259-8143                      FAX) 82-52-259-8149