

VANCRYL® 68-S

Resin Solution

September 2019



INTRODUCTION

VANCRYL 68-S resin solution is an aqueous solution of VANCRYL 68 acrylic resin, with ammonia used to affect the solution.

VANCRYL 68-S provides outstanding pigment wetting along with the viscosity stability needed for aqueous gravure and flexographic inks. The transfer properties and hold-out characteristics of inks prepared with this resin solution are excellent.

In coatings, VANCRYL 68-S provides high gloss, scuff resistance and hardness. VANCRYL 68-S is compatible with most acrylic vehicles and other vehicles such as maleic resins.

VANCRYL 68-S is effective as a protective colloid in the production of styrene-acrylic copolymer emulsions.

KEY PERFORMANCE PROPERTIES

- Outstanding pigment wetting
- Excellent transfer
- Good hold-out
- Low foam
- High gloss
- Compatible with most vehicles

TYPICAL PROPERTIES

VALUE

Appearance	Clear solution
Density, lbs/gal	8.6
Flashpoint	Non-combustible
Freeze-thaw stability	Stable
Molecular weight, M _w	20000
Non-Volatiles, %	30
pH	8.2
T _g , °C	57
Viscosity, 25°C, cP	3000
Viscosity, reduced solids, 25°C, cP	100
VOC, wt. %	<0.5

STARTING POINT FORMULATIONS

Flexographic Ink Base Grind	%
Phthalo blue pigment	32.0
VANCRYL 68-S resin solution	32.0
Water	35.0
KNOCKDOWN® 155 defoamer ⁽¹⁾	1.0

Finished Ink	%
Base Grind	29.0
VANCRYL 989 ⁽¹⁾ emulsion	58.0
Michem® Emulsion 32535 ⁽²⁾	8.0
Water	3.0
Diethylene glycol	1.0
KNOCKDOWN 155 defoamer	0.7
Ammonia	0.3

pH	8.6
#2 Zahn Viscosity, sec	33

High Gloss Coating	%
VANCRYL 989 emulsion	60.0
VANCRYL 68-S resin solution	25.0
Michem Emulsion 32535	5.0
KNOCKDOWN 155 defoamer	1.0
Water	9.0

pH	8.5
#2 Zahn Viscosity, sec	30

(1) Product of allnex

(2) Product of Michelman Inc.

www.allnex.com

Disclaimer: allnex Group companies ("allnex") exclude all liability with respect to the use made by anyone of the information contained herein. The information contained herein represents allnex's best knowledge but does not constitute any express or implied guarantee or warranty as to the accuracy, the completeness or relevance of the data set out herein. Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is suitable for any specific use, performance or result. Any unauthorized use of the product or information may infringe the intellectual property rights of allnex, including its patent rights. The user should perform his/her own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights or misappropriation of trade secrets of allnex and/or third parties remain the sole responsibility of the user.

Notice: Trademarks indicated with ®, TM or * as well as the allnex name and logo are registered, unregistered or pending trademarks of Allnex Netherlands B.V. or its directly or indirectly affiliated allnex Group companies.