



PLYAMUL® CPS 105

Description	An externally plasticized, hydroxyethyl cellulose stabilized polyvinyl acetate homopolymer	
Application	Binder for ready mix tape joint cement compounds	
Features	<ul style="list-style-type: none"> ◆ Excellent low temperature performance ◆ Excellent filler and pigment acceptance ◆ Excellent binder efficiency ◆ Superior workability ◆ Borax stable 	
Properties	Appearance	White liquid
	Nonvolatile Content, %	60.0 +/- 1
	pH	4.95 – 5.90
	Viscosity, cps (Brookfield, RV, #4/20rpm/25C°/77°F)	1500 - 3000
	Weight, U.S., Lbs./Gal.	8.9 – 9.3
	Glass Transition Temperature, °C by DSC	+13
Storage	Protect from freezing. Ideal storage temperature is 72°F. Stability at 72°F is >180 days.	
Packaging Forms	Available in 10,000- or 20,000-gallon railroad tank cars, 5,000-gallon tank trucks, totes or 55- gallon non-returnable fiber drums.	
Important Safety Information	Before using this or any other chemical product, be sure to read and understand the information on the Material Safety Data Sheet and Product Labels. Remain aware of potential hazards and follow all precautionary measures, handling instructions, and disposal considerations outlined in the MSDS and label.	

Rev 6/12

For help in a Chemical Emergency, call CHEMTREC at 1-800-424-9300

IMPORTANT: Information, specifications, procedures and recommendations provided ("information") are based on our experience and we believe this to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

NOTE TO USER: by ordering/receiving product you accept the **H.B. Fuller General Terms and Conditions of Sale** applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, the total aggregate liability of H.B. Fuller for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses arising out of or in connection with product supply.



H.B. Fuller

H.B. Fuller North America
inquiry@hbfuller.com
Contact us for details