

**DESCRIPTION**

Methoxy-functional silicone polyester resin

**KEY BENEFITS**

- excellent adhesion on aluminum, steel, and stainless steel
- low thermoplasticity
- excellent dishwasher detergent resistance

**SUITABILITY**

waterborne	solventborne
●	●

● not suitable   ● partly suitable   ● suitable

**TYPICAL APPLICATIONS**

- Heat-stable, decorative coatings
- Cook and bakeware
- Electric appliances

**TECHNICAL DATA**

<b>appearance</b>	clear to hazy colored liquid (product properties are not affected by haziness)
<b>delivery form</b>	liquid
<b>non-volatile content</b>	Approx. 60 %
<b>solvent</b>	methoxypropylacetate
<b>viscosity at 25 °C</b>	Approx 2000 mPas

**SOLUBILITY**

<b>Xylene</b>	<b>Dowanol MPA</b>
●	●
<b>Butylacetate</b>	<b>Cyclohexanone</b>
●	●

● not soluble   ● partly soluble   ● soluble

**PROCESSING INSTRUCTIONS**

- All heat-resistant pigments can be used due to the product's excellent pigment compatibility.
- In combination with alkoxy-functional resins, we do not recommend the use of alcohols or hydroxy-functional glycol ethers as solvents.
- Spray application.
- Roller application.

**CURING CONDITIONS**

250°C/15 min

**HANDLING & STORAGE**

When stored in an original unopened packaging between -10 and +40 °C, the product has a shelf life of at least 12 months from the date of manufacture. However, contact with tin (e.g. with metal containers) will shorten storage stability. Keep dry. Contact with moisture causes gelation.

**MSDS & REGULATORY INFORMATION**

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Resource Efficiency GmbH | Goldschmidtstraße 100, 45127 Essen, Germany | Telefon +49 201 173-2222 Telefax +49 201 173-1939 | [www.coating-additives.com](http://www.coating-additives.com)