

SUKOREZ SU-90
Hydrogenated DCPD hydrocarbon resin

Rev.07
1st/1/2014

SUKOREZ SU-90 is waterwhite thermoplastic resin obtained from polymerization and hydrogenation of cyclic ingredients. The major usages are tackifier for hot melt adhesive(HMA), hot melt pressure sensitive adhesive(HMP SA) and solvent based pressure sensitive adhesive(SBPSA), because of its good heat resistance and good compatibility with base polymers such as ethylene vinyl acetate(EVA), styrene block copolymer(SBC).

SPECIFICATIONS

Softening Point (Ring & Ball, °C)	85-95	ASTM E 28
Color (50% Toluene Solution, HAZEN)	Max.50	ASTM D 1209
Color Stability (@200°C, 5hrs, Ga.#)	Max.2	ASTM D 1544

TYPICAL PROPERTIES

Specific Gravity (20/20°C)	1.08	ASTM D 71
Softening Point (Ring & Ball, °C)	90	ASTM E 28
Color (50% Toluene Solution, HAZEN)	20	ASTM D 1209
Color Stability (@200°C, 5hrs, Ga.#)	<1	ASTM D 1544
Acid Value (KOH mg/g)	<0.1	ASTM D 974
Melt Viscosity BRF, @160°C, cps	260	ASTM D 3236
BRF, @180°C, cps	90	
Molecular Weight (GPC, Mw)	570	G.P.C

Kolon Industries and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

PACKAGING

SUKOREZ SU-90 is available in multi-ply paper bags of 25kgs net weight.

STORAGE

Pelletized forms of resins may block or lump in hot weather climates or if stored near heat sources. Inside storage is recommended and keep at temperature not exceeding 20°C

REGULATORY STATUS

SUKOREZ SU-90 is in compliance with the requirements of the U.S FDA for following sections.

- 175.105 Adhesives
- 175.125 Pressure sensitive adhesives
- 175.300 Resinous and polymeric coatings
- 175.320 Resinous and polymeric coatings for poly olefin films
- 176.170 Components of paper and paperboard in contact with aqueous and fatty foods.
- 176.180 Components of paper and paperboard in contact with dry food
- 177.1210 Closures with sealing gaskets for food containers
- 177.1520 Olefin polymers
- 177.2600 Rubber articles intended for repeated use



*HEAD OFFICE : 15TH FL., KOLON TOWER 1-23, BYULYANG-DONG GWACHEON-CITY KYUNGGI-DO, KOREA
TEL) 82-2-3677-6105 FAX) 82-2-3677-6191*

*ULSAN PLANT : SAPYUNG-RO 33, NAM-GU, ULSAN-CITY, KOREA
TEL) 82-52-259-8130 FAX) 82-52-260-1192*