

Product Information

Bayferrox® 340 G

Description

| | |
|---|---|
| Type | Black pigment |
| Field of application | Building industry |
| Delivery form | Microgranules |
| Chemical class | Synthetic iron oxide Fe ₃ O ₄ |
| Colour Index | Pigment black 11 (77499) |
| CAS-No. | 1317-61-9 |
| REACH registration no. | 01-2119457646-28-0000 |
| This product fulfills the requirements of EN 12878 category A (non reinforced materials). | |

Specification

| Colour values and tinting strength | | | |
|------------------------------------|---------------|------------|-----------------------|
| Standard for G | Bayferrox 340 | | |
| Year | 2006 | | |
| Binder | Cement mortar | | |
| | min | max | Test method |
| Color Consistency | | | |
| Color Difference ΔE^*_{ab} | | 1.5 | No. 015 ⁴¹ |
| Relative tinting strength [%] | 95 | 105 | No. 015 ⁴¹ |

Bayferrox® 340 G

Informative Technical Data (guide values)

| | | | Test method |
|--|---|------------|---|
| Pigment data | | | |
| Fe ₃ O ₄ Content [%] ⁵³ | > | 95.2 | Information about the determination of iron oxide ⁴¹ |
| Water-soluble content [%] | < | 2.3 | similar to DIN EN ISO 787-3:2000 |
| Bulk density [g/ml] | | 0.8 - 1.2 | similar to DIN EN ISO 787-11:1995 |
| Water absorption [g/100 g] | ~ | 36 | DIN 55608:2000 |
| pH value | | 5.0 - 10.0 | DIN EN ISO 787-9:1995 |
| Moisture content (after production) [%] | < | 2.0 | DIN EN ISO 787-2:1995 |
| Density [g/ml] | ~ | 4.6 | DIN EN ISO 787-10:1995 |
| Additional parameters concerning concrete technology | | | |
| Influence on setting time [min] Maximum difference between the initial setting time of mixes with/without pigment | < | 60 | similar to DIN EN 196-3:2005 |
| Influence on compressive strength [%] as strength loss based on unpigmented mix | < | 10 | similar to DIN EN 196-1:1994 |

⁴¹ Obtainable from LANXESS Deutschland GmbH, Business Unit Inorganic Pigments, [mailto: ipg.product-information@lanxess.com](mailto:ipg.product-information@lanxess.com)

⁵³ Minor elements may arise from the raw materials used. However, these are firmly bound to the crystal lattice as ions.

Bayferrox® 340 G

Packaging

The product is available in sacks or bulk bags. For further information please ask your local contact or send an enquiry by e-mail to [mailto: ipg.product-information@lanxess.com](mailto:ipg.product-information@lanxess.com)

Transport and Storage

| | | | | | |
|--|--|--|---------|-----------------------------|---------|
| General storage conditions: | Protect against weathering. Store in a dry place and avoid extreme fluctuations in temperature. | | | | |
| Maximum storage temperature: | When storing large quantities of pigments, temperatures above 80 °C must be avoided as an alteration (oxidation) of the pigment may be caused by heat. | | | | |
| Special conditions for opened packaging: | Close bags after use to prevent the absorption of moisture and contamination. | | | | |
| Shelf life: | <p>This product has an excellent shelf life. We recommend that this product is used within ten years of the date of manufacture and limit our product warranty to this period. During the first ten years after the date of manufacture we are able to ensure compliance with this specification, provided the material has been stored as stated above and the packaging materials remain undamaged. It must be taken into account that the packaging mean can have a shelf life considerably shorter than the one for this product. All recommendations and warnings given on the packaging must strictly be adhered to. Deviations from storage conditions can lead to undesired changes on side of the packaging materials. These succumb to ageing which may also lead to compromising their capability. Concerning their estimated service life we differentiate between the following packaging materials:</p> <table><tr><td>All kinds of bags (Paper and PE)</td><td>5 years</td></tr><tr><td>All kinds of Bulk bag</td><td>3 years</td></tr></table> <p>With respect to our Bulk Bags we recommend to avoid UV-radiation because the sewing material of the lifting loops is stabilized against degradation by UV-radiation for appr. 1000 h incident sun radiation for the climate of Central Europe. A more intense sun radiation can shorten this period significantly. In cases of doubt the lifting loops must be checked thoroughly.</p> | All kinds of bags (Paper and PE) | 5 years | All kinds of Bulk bag | 3 years |
| All kinds of bags (Paper and PE) | 5 years | | | | |
| All kinds of Bulk bag | 3 years | | | | |

Safety

The product is not classified as dangerous under the relevant EC Directives and corresponding national regulations valid in the individual EU member states. It is not dangerous according to transport regulations.

In countries outside the EU, compliance with the respective national legislation concerning the classification, packaging, labelling and transport of dangerous substances must be ensured. The safety data sheet should be observed. This contains information on handling, product safety and ecology. The safety data sheet is available at www.bayferrox.de.

Bayferrox® 340 G

Status of registration (not specified)

| The components of this product are listed on the following inventories: | | | | |
|---|----------------|----------------|--------------------|-----------------------|
| Europe: EINECS | USA: TSCA | Canada: DSL | Australia: AICS | New Zealand: NZIOC |
| Philippines: PICCS | Japan: METI | Korea: ECL | China: IECSC | Taiwan: NECSI |