

CYMEL[®] UI-21-E resin

PRODUCT DESCRIPTION

CYMEL UI-21-E resin is a partially iso-butylated urea resin supplied in ethanol. It has been designed for a wide range of high build, low odor industrial wood finishes. CYMEL UI-21-E resin is not suitable for exterior applications.

BENEFITS

- Fast drying
- Low odor

APPLICATION AREAS

- Industrial wood finishes

PHYSICAL PROPERTIES

Property	Range	Method
Appearance	Clear to hazy liquid	Visual
Non-volatile by wt.	76-80%	Pan, 1 hr/100°C
Viscosity, 23°C	3500 – 4500 mPa-s	Dynamic
Free formaldehyde	~0.8%	Sulfite
Color, APHA	< 50	ISO 6271

SOLUBILITY

Alcohols	Complete
Esters	Complete
Ketones	Complete
Aromatic hydrocarbons	Partial
Aliphatic hydrocarbons	Partial
Water	Insoluble

COMPATIBILITY

Acrylic resins	Medium
Alkyd resins	Good
Polyester resins	Good
Nitrocellulose	Good
Cellulose acetate butyrate	Good
Polyvinyl butyrate	Good

BACKBONE POLYMER SELECTION

CYMEL UI-21-E resin is a very effective crosslinking agent for backbone polymer resins containing hydroxyl functional groups, such as alkyd, polyester or acrylic resins. The optimum level of CYMEL UI-21-E resin in an acid curing wood coating formulation should be in the range of 25-35% on total resin solids. To obtain coatings with optimum resistance properties, addition of a melamine resin, such as CYMEL MB-98, at levels of 5-10% on total resin solids is recommended.

FORMULATING

If acetone is being considered for reduction of calculated VOC, extended storage stability testing of formulated coatings with various levels of acetone should be completed to ensure acceptable color stability.

CATALYSIS

CYMEL UI-21-E resin responds to both weak acids and sulfonic acid catalysts, like CYCAT[®] 4040 catalyst. Generally, 6-10% CYCAT 4040 catalyst on total resin solids of the formulation is sufficient to obtain fast drying behavior at room temperature.

POT LIFE

To extend catalyzed pot life of the formulation, addition of primary alcohols, such as n-butanol and ethanol, is required at concentrations of 10-25% on total resin solids. Faster evaporating alcohols will improve speed of dry.

STORAGE STABILITY

CYMEL UI-21-E resin has a shelf life of 24 months from date of manufacture when stored at temperatures between 5°C and 30°C. Although lower temperatures are not detrimental to stability, the viscosity of the product will increase making the resin more difficult to pump or pour. Product viscosity can be returned to normal by gentle re-warming, however, care should be taken to avoid excessive localized heating as this can cause irreversible viscosity increase.

• Worldwide Contact Info: www.allnex.com •

Disclaimer: Allnex Group companies ("Allnex") decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents Allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of Allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any Allnex and/or third party intellectual property rights. The user should perform its own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of Allnex and/or third parties remains the sole responsibility of the user.

Notice: Trademarks indicated with the ®, ™ or * are registered, unregistered or pending trademarks of Allnex Belgium SA or its directly or indirectly affiliated Allnex Group companies.

April 2015