

HIKOTACK P-120

Rev.08 1st/5/2011

Aromatic hydrocarbon resin

HIKOTACK P-120 is pale yellow thermoplastic resin obtained from polymerizing unsaturated aromatic olefins and diolefins derived from the process of thermal cracking of naphtha. The major usages are vehicles for the paint and ink products, tackfier for solvent based adhesive (CR Adhesive), water repellent agent, concrete curing agent, and binder for asphalt.

SPECIFICATIONS

Softening Point (Ring & Ball, °C)	115-125	ASTM E 28
Color (50wt% Solution in Toluene, Ga.#)	Max.8	ASTM D 1544
Acid Value (KOH mg/g)	Max.0.1	ASTM D 974
Bromine Number (Br.cg/g)	Max.30	ASTM D 1159
TYPICAL PROPERTIES		
Specific Gravity (20/20°C)	1.08	ASTM D 71
Softening Point (Ring & Ball, °C)	120	ASTM E 28
Color (50wt% Solution in Toluene, Ga.#)	4	ASTM D 1544
Color Stability (@200°C, 3hrs, Ga.#)	9	Molten Resin
Acid Value (KOH mg/g)	0.04	ASTM D 974
Bromine Number (Br.cg/g)	18	ASTM D 1159
Melt Viscosity BRF, @160°C, cps	4000	ASTM D 3236
@180°C, cps	750	
Molecular Weight (GPC, Mw)	1,800	G.P.C

Kolon Industries and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determation of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

PACKAGING

HIKOTACK P-120 is available both in big bags of 500kgs net weight and in multi-ply paper bags of 25kgs net weight.

STORAGE

Pelletized forms of resins may block or lump in hot weather climates or if stored near heat sources. Inside storage is recommended and keep at temperature not exceeding 30°C

REGULATORY STATUS

HIKOTACK P-120 is in compliance with the requirements of the U.S FDA for following sections.

175.105	Adhesives
175.300	Resinous and polymeric coatings
177.1210	Closures with sealing gaskets for food containers
177.2600	Rubber articles intended for repeated use



HEAD OFFICE: 10 TH FL., KOLON TOWER 1-23, BYULYANG-DONG GWACHEON-CITY KYUNGGI-DO, KOREA

TEL) 82-2-3677-6120 FAX) 82-2-3677-6191

ULSAN PLANT: 499-58, BUGOG-DONG, NAM-GU, ULSAN-CITY, KOREA