

## Castung™ 403 Z-3

### product identification

Description	Castung 403 Z-3 is a bodied dehydrated castor oil (DCO) that can be used with pure and modified phenolic resins to impart alkali resistance for can linings, corrosion resistant coatings, traffic paints, ink vehicles and marine finishes. The high viscosity Castung 403 Z-3 will yield faster processing and drying times than Castung 103 G-H. Castung 403 Z-3 is excellent for formulating alkyd and copolymer resins, where dehydrated castor oil is well known for its non-yellowing and outstanding color retention characteristics.
-------------	-----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------

### typical properties

Appearance	Clear, amber liquid
Color, Gardner	6
Iodine Value	123
Viscosity, Gardner (25 °C)	Z-3
Specific Gravity, @ 25/25 °C	0.949

Revised 08-JANUARY-24

Consult the Safety Data Sheet for hazard and regulatory information

Information contained in this technical data sheet is believed to be accurate. Aurorium assumes no liability and makes no warranty or representation that the information is correct or complete. Final determination of suitability of any material and issues of patent infringement is the sole responsibility of the user who alone knows the conditions of intended use. Our customers should ensure that any product incorporating an Aurorium ingredient is safe for its intended use pursuant to applicable law and that any necessary disclosures to consumers have been made.

© 2023 Aurorium Holdings LLC. All rights reserved. ™ indicates a trademark registered in the United States and/or elsewhere

201 North Illinois Street, Suite 1800, Indianapolis, IN 46204 USA • [ask@aurorium.com](mailto:ask@aurorium.com)

[aurorium.com](http://aurorium.com)

