

CYMEL[®] 1141 resin

October 2017



PRODUCT DESCRIPTION

CYMEL 1141 resin is a highly methylated/iso-butylated, carboxy-modified melamine crosslinker supplied in iso-butanol. CYMEL 1141 resin is especially designed for electro-deposition primer formulations requiring excellent corrosion and resistance properties. CYMEL 1141 contains chelating groups which can form colored compounds with heavy metal ions such as iron and zinc. For that reason it is recommended to use CYMEL 1141 resin only in dark single coat applications or primers and not in pastel colors.

BENEFITS

- Electrodeposition properties
- Adhesion properties
- Corrosion resistance

APPLICATION AREAS

- Anodic electrodeposition
- Cathodic electrodeposition
- High solids primer formulations

PHYSICAL PROPERTIES

Property	Range	Method
Appearance	Clear Liquid	ASTM E284
Non-volatile by wt.	83-87%	DIN 55671 (Foil, 45 min/45°C)
Viscosity, 25°C	W-Y	ASTM D1545 (Gardner-Holdt)
Free formaldehyde	<0.4%	Sulfite Titration
Color, Gardner	≤ 3	DIN EN ISO 4630-1

SOLUBILITY

Alcohols	Complete
Esters	Complete
Ketones	Complete
Aromatic hydrocarbons	Partial
Aliphatic hydrocarbons	Insoluble
Water	Insoluble

COMPATIBILITY

Acrylic resins	Very good
Alkyd resins	Very good
Polyester resins	Very good
Epoxy resins	Very good

www.allnex.com

BACKBONE POLYMER SELECTION

CYMEL 1141 resin contains mainly methoxymethyl and butoxymethyl functionalities making it a very effective crosslinker for backbone polymer resins containing hydroxyl, amide, or carboxyl functional groups, such as found on alkyd, polyester or acrylic resins. CYMEL 1141 is compatible with a wide range of backbone polymers providing films with superior adhesion and resistance properties. The effective equivalent weight of CYMEL 1141 typically ranges from 150-250 g/eq, however, its optimum loading should be determined experimentally for each formulation with consideration of the performance properties to be optimized.

CATALYSIS

CYMEL 1141 resin will respond best to sulfonic acid catalysts, like CYCAT[®] 4040 catalyst or the amine-blocked version, CYCAT 4045 catalyst. Generally, 0.5 to 1.0% catalyst solution on total binder solids of the formulation is sufficient to provide good cure at baking schedules of 20 minutes at 120°C to 160°C. Higher concentrations might be necessary if there are basic pigments or additives present in the formulation. Waterborne systems generally require temperatures of 150°C and higher to effect cure.

FORMULATION STABILITY

The stability of formulated systems containing CYMEL 1141 resin can be enhanced by the addition of alcohols, amines or a combination of these. Low molecular weight primary alcohols such as methanol and n-butanol are most effective. Recommended amines are dimethylethanolamine (DMEA), triethylamine (TEA), or 2-amino-2-methyl-1-propanol (AMP) at a concentration of 0.5-1.0% on total binder solids. Package stability can also be enhanced by the use of a blocked acid catalyst such as CYCAT 4045 catalyst. For waterborne systems a pH of 7.5-8.5 should be maintained for adequate stability.

STORAGE STABILITY

CYMEL 1141 resin has a shelf life of 1080 days from the date of manufacture when stored at temperatures below 32°C. Although lower temperatures are not detrimental to stability, its viscosity will increase, possibly making the resin difficult to pump or pour. The viscosity will reduce again on warming, but care should be taken to avoid excessive local heat, as this can cause an irreversible increase in viscosity.

Disclaimer: allnex Group companies ('allnex') decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any allnex and/or third party intellectual property rights. The user should perform his/her own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of allnex and/or third parties remains the sole responsibility of the user.

Notice: Trademarks indicated with [®], [™] or * as well as the allnex name and logo are registered, unregistered or pending trademarks of Allnex IP s.à.r.l. or its directly or indirectly affiliated allnex Group companies.