

VERSAL YELLOW 8GN



Characteristic

C. I.	Pigment Yellow 128
C. I. No.	20037
CAS No.	79953-85-8
Chemical Class	Disazo Cond.

Properties

Oil Absorption [ml/100 g]	80
Density [g/cm ³]	1.5
Bulking Volume [l/kg]	7.5

Fastness

Linseed Oil	5
White Spirite	5
DEHT	5
Xylene	5
Acetone	3-4
Butylacetate	4-5
Ethanol	5
Water	5
HCl 2.5%	5
NaOH 2.5%	5
Light - Full Shade	7-8
Light - 1/1	7
Light - 1/3	7
Weather - Full Shade	4
Weather - 1/1	3-4
Weather - 1/3	3-4
Overspray	5
Heat Resistance [°C]	P 260
Migration	5

P - in Plastics

Application Possibilities

Printing Inks - Nitrocellulose	<input type="checkbox"/>
Printing Inks - Water based	<input checked="" type="checkbox"/>
Printing Inks - UV Curing	<input checked="" type="checkbox"/>
Paints - Decorative	<input checked="" type="checkbox"/>
Paints - Industrial	<input checked="" type="checkbox"/>
Paints - Powder Coatings	<input checked="" type="checkbox"/>
Plastics - Polyolefines	<input checked="" type="checkbox"/>
Plastics - PVCp	<input checked="" type="checkbox"/>
Plastics - PP Fibers	<input checked="" type="checkbox"/>
<input checked="" type="checkbox"/> main application	<input type="checkbox"/> side application

Other Informations

Shelf Life	48 months
------------	-----------

Testing methods
Density

- determined by ČSN EN ISO 787-10: 1997 (67 0520) in g/cm^3

Bulking Volume

- denotes the volume of 1 kg of loosely poured pigment, expressed in litres

Oil Absorbtion

- determined by ČSN EN ISO 787-5: 1997 (67 0520) in ml/100 g pigment

Fastness to Solvents

- colouring of solvent after 24 h at 20 °C according to ISO grey scale is determined; degree 1 denotes the lowest fastness, degree 5 the highest one

Fastness to Reagents

- colouring of reagents after 24 h at 20 °C according to ISO grey scale is determined; degree 1 denotes the lowest fastness, degree 5 the highest one

Light Fastness - Xenotest

- determined by ČSN EN ISO 105-B02: 2000 (80 0147) and evaluated in 1/3 and 1/1 of standard depth and in full shade; determined according to blue scale, by it degree 1 denotes the lowest fastness, degree 8 the highest one

Weathering Fastness - Xenotest

- determined by ČSN EN ISO 105-B04: 1998 (80 0171) and evaluated in 1/3 and 1/1 of standard depth and in full shade; determined according to grey scale, by it degree 1 denotes the lowest fastness, degree 5 the highest one

Overspray Fastness

- assessment of bleeding into a white nitrocellulose combination lacquer for 60 min. at 70 °C against ISO grey scale; by it degree 1 denotes the lowest fastness, degree 5 the highest one

Heat Resistance

- the values quoted indicate up to what temperature the pigments do not significantly alter; these are guide values which can be influenced by the binder used and the period of exposure to high temperature

Migration Fastness

- assessment of bleeding into a white polyvinylchloride sheet for 24 h at 70 °C against ISO grey scale; by it degree 1 denotes the lowest fastness, degree 5 the highest one; no data means that the pigment is not recommended for dyeing of PVC

Fastness to plasticizers

- colouring of plasticizer (diethylhexylterephthalate) after 24 h at 20 °C according to ISO grey scale is determined; degree 1 denotes the lowest fastness, degree 5 the highest one