

Specifications for
BRITOL® 9T White Mineral Oil, Technical Grade

<u>PROPERTIES GUARANTEED</u>	<u>TEST METHOD</u>	<u>LIMITS</u>
SPECIFIC GRAVITY @ 25°C/25°C	ASTM D4052	0.835/0.862
KIN. VISCOSITY @ 40°C, CST	ASTM D445	14.5/17.0
UV ABSORBANCE	21CFR 178.3620(B)	PASS
COLOR, SAYBOLT	ASTM D156	20 Min.

TYPICAL PROPERTIES FOR BRITOL® 9T White Mineral Oil, Technical Grade

<u>PROPERTIES</u>	<u>TEST METHOD</u>	<u>TYPICAL VALUE</u>
WT. / GAL. @ 60°F	ASTM D4052	7.1

The information contained herein is correct to the best of our knowledge. Your attention is directed to the pertinent Material Safety Data Sheets for the products mentioned herein. All sales are subject to Sonneborn's standard terms and conditions of sale, copies of which are available upon request and which are part of Sonneborn's invoices and/or order acknowledgments. Except as expressly provided in Sonneborn's standard terms and conditions of sale, no warranty, express or implied, including warranty of merchantability or fitness for particular purpose, is made with respect to the products described herein. Nothing contained herein shall constitute permission or recommendation to practice any invention covered by a patent without a license from the owner of the patent.