

Product Information

Bayferrox® 120 M

Description

| | |
|------------------------|---|
| Type | Red pigment - High Performance micronised |
| Delivery form | Powder |
| Chemical class | Synthetic iron oxide α - Fe_2O_3 |
| Colour Index | Pigment red 101 (77491) |
| CAS-No. | 1309-37-1 |
| REACH registration no. | 01-2119457614-35-0000 |

Specification

| Colour values and tinting strength | | | | |
|---|-------------------|-----|--|---|
| Standard | Bayferrox 120 M | | | |
| Year | 2009 | | | |
| Binder: Test paste based on a non drying alkyd resin ⁴⁶ | Full shade | | Reduction with titanium dioxide Tronox® R-KB-2 (1 : 5) ⁴⁵ | Test method No. 001 of 1995-04- 28 ⁴¹ |
| ΔL^* | -0.4 | 0.4 | | |
| Δa^* | -0.8 | 0.8 | -0.5 | 0.5 |
| Δb^* | -0.9 | 0.9 | -0.5 | 0.5 |
| ΔC_{ab}^* | -0.8 | 0.8 | -0.6 | 0.6 |
| ΔH_{ab}^* | -0.8 | 0.8 | -0.6 | 0.6 |
| ΔE_{ab}^* | | 1.0 | | 0.8 |
| Relative tinting strength [%] | | | 97 | 103 |

Specification

| Dispersibility | min | max | Test method |
|---|------------|------------|-------------------------------------|
| Binder Alkydal F 681 75 % in white spirit | | | |
| Grindometer values [μm] (dissolver mill base) | | 20/35/50 | No. 004 of 1995-05-15 ⁴¹ |
| Technical Data | min | max | Test method |
| water-soluble content [%] | | 0.5 | as per DIN EN ISO 787-3:1995 |
| Sieve residue (0.045 mm sieve) [%] | | 0.002 | as per DIN 53195:1990 |
| pH value | 5 | 8 | as per DIN EN ISO 787-9:1995 |

Bayferrox® 120 M

Informative technical data (guide values)

| | | | Test method |
|---|---|-----------|---|
| α - Fe ₂ O ₃ Content [%] ⁵³ | > | 94.1 | information about the determination of iron oxide ⁴¹ |
| Loss on ignition at 1000 °C, 0.5 h [%] | < | 0.7 | similar to DIN 55 913:1972, sheet 2 |
| Moisture content (after production) [%] | < | 0.3 | as per DIN EN ISO 787-2:1995 |
| Particle shape | | spherical | Electron micrographs |
| Predominant particle size [μ m] | ~ | 0.12 | Electron micrographs |
| Oil absorption [g/100 g] | ~ | 28 | as per DIN EN ISO 787-5:1995 |
| Tamped density [g/ml] | | 0.9 - 1.3 | as per DIN EN ISO 787-11:1995 |
| Density [g/ml] | ~ | 5.0 | as per DIN EN ISO 787-10:1995 |

Bayferrox® 120 M

Packaging

The product is available in sacks or bulk bags. For further information please ask your local contact or send an enquiry by e-mail to [mailto: ipg.product-information@lanxess.com](mailto:ipg.product-information@lanxess.com)

Transport and storage

| | |
|--|--|
| General storage conditions: | Protect against weathering. Store in a dry place and avoid extreme fluctuations in temperature. |
| Special conditions for opened packaging: | Close bags after use to prevent the absorption of moisture and contamination. |
| Shelf life: | If stored under the correct conditions (no climatic influence, kept dry and no extreme fluctuations in temperature) our products have an excellent shelf life. However, due primarily to the limited durability of the packaging, we recommend that the product is used within 5 years of the date of manufacture and our product warranty is limited to this period. During the first five years after the date of manufacture we are able to ensure compliance with our specification, provided the material has been stored correctly and the packaging materials remain undamaged. |

Safety

| | |
|------------------------|---|
| Classification | The product is not classified as dangerous under the relevant EC Directives and corresponding national regulations valid in the individual EU member states. It is not dangerous according to transport regulations. |
| Additional Information | In countries outside the EU, compliance with the respective national legislation concerning the classification, packaging, labelling and transport of dangerous substances must be ensured. The safety data sheet should be observed. This contains information on handling, product safety and ecology. The safety data sheet is available at www.bayferrox.de . |

Bayferrox® 120 M

Information concerning European food contact regulations (not specified)

This product complies with the purity requirements of the following legal regulations or is listed on the mentioned positive lists.

General remark

As the food contact regulations of each country may differ, it is the responsibility of the manufacturer of the finished articles to ensure compliance with the respective country's regulation (e.g. migration or extraction limits).

| | |
|-------------------------------------|---|
| European Union (Council of Europe) | Resolution AP (89) 1 on the use of colorants in plastic materials coming into contact with food. (requirements correspond with those of BfR Recommendation IX.) |
| Germany | Recommendation IX of the Federal Institute for Risk Assessment (BfR) dated 01. Jan 2010 |
| Belgium | Koninklijk Besluit dated 11.5.1992; Warenwetgeving (1), aanvulling nr. 18 - September1992 |
| France | Circulaire 176 dated 2.12.1959, published in the Journal Officiel of 30.12.1959 incl. amendments. |
| Netherlands | Warenwet/Regeling Verpakkingen - en gebruiksartikelenbesluit; Uitvoeringsvoorschriften CIII-55, entered into force on 21.8.1991. As well as defining the content of soluble heavy metals in pigments, this regulation specifies maximum permissible migration values for the pigmented articles. |
| Spain | Resolucion dated 4.1L1982 (BOE 282 of 24.11.1982) in accordance with Article 5 of Royal Decree 211/1992 of March 5, 1992. All colorants are permitted which conform with the migration values defined in Appendix III of the Resolucion. Pigments used in foodcontact applications must be notified to the Health Ministry. All Bayferrox pigments which satisfy BgVV Recommendation IX can be used in Spain. |

Information concerning Non-European food contact regulations (not specified)

This product complies with the purity requirements of the following legal regulations, or is listed on the mentioned positive lists

General remark

As the food contact regulations of each country may differ, it is the responsibility of the manufacturer of the finished articles to ensure compliance with the respective country's regulation (e.g. migration or extraction limits)

| | |
|-----------|--|
| Australia | Australian Standard 2070.6 (1984) |
| USA | According to § 178.3297 (Colorants for Polymers) |

Bayferrox® 120 M

Status of registration (not specified)

| The components of this product are listed on the following inventories: | | | | |
|---|----------------|----------------|--------------------|-----------------------|
| Europe: EINECS | USA: TSCA | Canada: DSL | Australia: AICS | New Zealand: NZIOC |
| Philippines: PICCS | Japan: METI | Korea: ECL | China: IECSC | Taiwan: NECSI |

⁴¹obtainable from LANXESS Deutschland GmbH, Business Unit Inorganic Pigments, Fax +49-2151-88-9599-4139, mailto: ipg.product-information@lanxess.com

⁴⁵Colour values after matching of the tinting strength parameter Y, i.e. $\Delta L^*=0$

⁴⁶similar to wet system DIN 55983:1983

⁵³Minor elements may arise from the raw materials used. However, these are firmly bound to the crystal lattice as ions.