

Intermediate

TEGOMER® E-Si 2330

DESCRIPTION

Epoxy-functional polydimethylsiloxane

KEY BENEFITS

- hydrophobization
- flexibilization
- epoxy reactive

TECHNICAL DATA

active matter content	100 %
appearance	liquid
epoxy equivalent weight (calculated on non-volatile content)	Approx 1200 g
molecular weight	Approx 2400 g/mol

PROCESSING INSTRUCTIONS

Limited miscibility with aromatic hydrocarbons.

HANDLING & STORAGE

When stored in an original unopened packaging between -10 and +40 °C, the product has a shelf life of at least 24 months from the date of manufacture. However, contact with tin (e.g. with metal containers) will shorten storage stability.

MSDS & REGULATORY INFORMATION



This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Resource Efficiency GmbH | Goldschmidtstraße 100, 45127 Essen, Germany | Telefon +49 201 173-2222 Telefax +49 201 173-1939 | www.coating-additives.com