

Technical data sheet : MK-140

1. Description

MKOREZ[®] MK-140 is made from highly purified monomers such as styrene and/or alpha methyl styrene. This pureness of raw materials can make the resin has water white color with high aromaticity than that of conventional hydrogenated resins at the same time.

This has good heat stability and excellent potential as a modifier in high shear adhesive compounds based on SBCs (SIS,SBS or SEBS etc)

This can be also used as additive in other kinds of adhesive or various elastomeric compounds as well.

2. Product specifications

• Softening Point (Ring & Ball, °C)	135-145	ASTM E 28
• Color (50% Toluene Solution, HAZEN)	Max.30	ASTM D 1209

3. Typical properties

• Softening Point (Ring & Ball, °C)	137-141	ASTM E 28
• Glass transition temperature (Tg, °C)	90	DSC
• Color (50% Toluene Solution, HAZEN)	13-23	ASTM D 1209
• Melt Viscosity BRF, @160°C, cps	125,300	ASTM D 3236
BRF, @180°C, cps	15,460	
• Molecular Weight Mw	3,800-5,000	G.P.C

Kolon Industries and its marketing affiliates shall not be responsible for the use of this information, or of any product, method or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

4. Packaging & Storage

• **Packaging**

available both in multi-ply paper bags of 25kgs net weight and in big bags.

• **Storage**

Pelletized forms of resins may block or lump. It is recommended,

- to store inside and keep cool condition
(In case of softening point over 100°C, max 30°C / In case of softening point below 100°C, max 25°C)
- not stacking pallets
- to avoid sunlight

Especially, low softening point resins (below 100°C) has a higher possibility of blocking due to the nature of product. Therefore, we strongly recommend that keep storing in more strict conditions.

5. Shelf life

The shelf life can be affected by storage and handling conditions. When products are stored in the original unopened container in an enclosed area and protected from contamination, moisture and extreme temperatures, the shelf life of MKOREZ[®] MK-140 is two years from the date of manufacture. Shelf life is a guide not an absolute value, and KOLON doesn't control end uses and storage conditions at customers. Therefore, the product should be reanalyzed for properties at the end of its shelf life to see if it meets specification for use.

Contact

- HEAD OFFICE : 9TH FL, ONE&ONLY TOWER, MAGOKDONG-RO 110, GANGSEO-GU
SEOUL, KOREA (07793)
TEL) 82-2-3677-6121 FAX) 82-2-3677-6191
- YEOSU PLANT : SANDANJUNGANG-RO 213, YEOSU-SI, JEOLLANAM-DO, KOREA (59610)
TEL) 82-61-690-9860 FAX) 82-61-690-9882