

3M Advanced Materials Division

# 3M™ Glass Bubbles K20HS

## Introduction

3M™ Glass Bubbles K20HS are high-strength additives for polymers made from a water-resistant and chemically stable soda-lime borosilicate glass. These hollow glass bubbles can be compounded with a variety of polymers to reduce the overall density of the composite. These composites can be incorporated into deep sea syntactic foam buoyancy modules to improve uplift properties of the system at minimal foam volumes.

The high strength of K20HS glass bubbles can withstand both the high processing shear forces of polymer mixing and the pressure of seawater in many applications. The K20HS glass bubbles have isostatic crush strengths of 750 psi with a minimum of 90% survival. These general-purpose microspheres offer very good strength-to-density ratio, making them suitable for a variety of uses, including:

- Oil and Gas
- Coatings
- Adhesives
- Mastics
- Sealants
- Thermoset Resin Systems

**Flow properties:** 3M glass bubbles K20HS will remain free flowing for at least two years from the date of manufacture when stored in the original, unopened container in accordance with the recommended storage conditions. (See storage recommendations at right).

## Material Description (Not for specification purposes.)

| Property           | 3M™ Glass Bubbles K20HS        |
|--------------------|--------------------------------|
| Shape              | Hollow spheres with thin walls |
| Composition        | Soda-lime-borosilicate glass   |
| Color, unaided eye | White, powdery                 |

## Typical Physical Properties (Not for specification purposes.)

| Property   | 3M™ Glass Bubbles K20HS |
|--|-------------------------|
| Crush strength, 90% survival by volume (psi)           | 750                     |
| True density (g/cc)                                    | 0.20                    |
| Packing factor (bulk density to true particle density) | 62%                     |
| pH (at 5 wt% loading in water)                         | 9.5                     |
| Average diameter (microns)                             | 60                      |
| Softening point (°C)                                   | 600                     |
| Flotation (density <1.0 g/cc)                          | 94%                     |
| Volatile content (by weight)                           | 0.5%                    |

3M Advanced Materials product realization process and manufacturing sites are aligned to ISO 9001 Quality Systems. Test data is generated by following documented procedures and test methods.

**Glass bubble breakage:** Breakage may occur if the product is severely processed. To minimize breakage, minimize exposure to high shear processes and point contact shear such as gear pumps and 3-roll mills. When adding to an extrusion process, the material should be added downstream of the feed hopper via a side stuffer or top feeder (similar to adding glass fiber). Contact 3M technical service or your equipment vendor for assistance if breakage is suspected.

## Packaging

**Small Box** : 30 kg

**Bulk Bag** : 300 kg

## Product Storage, Handling and Safety

**Storage:** Ideal storage conditions include unopened cartons in a dry and temperature-controlled warehouse. Extended exposure of 3M glass bubbles K20HS boxes to high humidity and/or conditions susceptible to condensation may result in some amount of “caking” of the glass bubbles.



## Product Storage, Handling and Safety (continued)

To minimize the potential for caking and thereby maximize storage life, the following suggestions are offered:

1. Carefully re-tie opened bags immediately after use.
2. If the polyethylene bag is punctured during shipping or handling, seal the hole as soon as possible or insert the contents into an undamaged bag.
3. During hot and/or humid months, store boxes in the driest, coolest space available.

If controlled storage conditions are unavailable, carry a minimum inventory, and process on a first in/first out basis.

**Handling:** Due to the low weight and small particle size of 3M™ Glass Bubbles K20HS, dusting may occur while handling and processing. To minimize the dusting potential during handling, consider the following:

- Do not open glass bubbles packages until ready to use.
- Upon opening, have local exhaust ventilation near the opening to pull away airborne particles. (Dust collection equipment may be required – check local OSHA and other applicable regulations.)

- Remove glass bubbles with a suction “wand” (with slight positive pressure aeration) and transfer to a closed mixing tank inside fully contained piping. If a closed mixing tank is not available, use dust collection equipment as close as practical to the point of entry. Pneumatic conveyor systems have been used successfully to transport glass bubbles without dusting from shipping containers to batch mixing equipment. Equipment vendors should be consulted for recommendations.

- Static eliminators should be used to prevent static buildup.

**Safety:** For worker protection, please consider the following:

- Use safety glasses with side shields for eye protection.
- An air-purifying respirator suitable for particulates may be selected for protection after an optional exposure assessment is performed for your specific application. (For additional information about personal protective equipment, refer to the product Safety Data Sheet.)

- Use with appropriate local exhaust ventilation/dust collection in the work area.
- Refer to the 3M™ Glass Bubbles Safety Data Sheet for additional safety information.

### Additional Information

3M glass bubbles are supported by global sales, technical and customer service resources, with fully-staffed technical service laboratories in the U.S., Europe, Japan, Latin America and Southeast Asia. Users benefit from 3M’s broad technology base and continuing attention to product development, performance, safety and environmental issues.

For additional technical information on 3M glass bubbles in the United States, call 3M Advanced Materials Division, **800-367-8905**. For other 3M global offices, and information on additional 3M products, visit our web site at: [www.3M.com/glassbubbles](http://www.3M.com/glassbubbles).

**Warranty, Limited Remedy, and Disclaimer:** Many factors beyond 3M’s control and uniquely within user’s knowledge and control can affect the use and performance of a 3M product in a particular application. User is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user’s method of application. User is solely responsible for evaluating third party intellectual property rights and for ensuring that user’s use of 3M product does not violate any third party intellectual property rights. Unless a different warranty is specifically stated in the applicable product literature or packaging insert, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OF NON-INFRINGEMENT OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M’s option, replacement of the 3M product or refund of the purchase price.

**Limitation of Liability:** Except where prohibited by law, 3M will not be liable for any loss or damages arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

**Technical Information:** Technical information, recommendations, and other statements contained in this document or provided by 3M personnel are based on tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed. Such information is intended for persons with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.



**3M Advanced  
Materials Division**

3M Center  
St. Paul, MN 55144 USA

Phone 1-800-367-8905

Web [www.3M.com/glassbubbles](http://www.3M.com/glassbubbles)

3M is a trademark of 3M Company.  
Used under license by 3M  
subsidiaries and affiliates.

Please recycle. Printed in USA. ©  
3M 2018. All rights reserved.  
Issued: October 2018