Polycin D-265Technical Data Sheet



Product Identification

Polycin D-265 is a 100% solids castor oil based derivative designed for use as a polyol or reactive diluent in polyurethane systems. Polycin D-265 will impart flexibility and improved pigment wetting into many polyurethane systems. Polycin D-265, as a reactive diluent, will allow for VOC reduction while imparting the beneficial properties of castor oil derivatives such as improved flow and levelling.

	<u>Property</u> <u>Value</u>		
Physical	Acid Value 1		
Properties	Appearance Pale yellow liquid		
	olor, Gardner 2 – 3, typical		
	Density, lbs./gal, 25°C 8.05		
	Equivalent Weight 212		
	Functionality 2		
	Hydroxyl Value 265		
	Moisture, % 0.02		
	Non-Volatile, % 100		
	Specific Gravity, 25°C/25°C 0.968		
	Viscosity, cP @ 25°C 370		
Applications	 Formulation of 100% solids high performance 	Formulation of 100% solids high performance polyurethane coatings	
	 Low VOC UV resistant 2-component industr and thermosetting OEM coatings 	Low VOC UV resistant 2-component industrial maintenance coatings and thermosetting OEM coatings	
	·	Property improvements such as; flexibility, adhesion, moisture resistance, and chemical resistance in coatings, adhesives, sealants, and elastomeric formulations	
	 Low VOC force dry and bake topcoats and metal 	Low VOC force dry and bake topcoats and primers for plastics and metal	
	 Low viscosity, solvent free pigment disper melamine bake systems. 	Low viscosity, solvent free pigment dispersions for urethane and melamine bake systems.	
Reduced	 VOC and viscosity reduction in coatings, adhe 	VOC and viscosity reduction in coatings, adhesives and sealants	
	 Urethane Intermediates, Polymers 	Urethane Intermediates, Polymers	

For toxicity or regulatory information please consult the Material Safety Data Sheet.

Information contained in this technical data sheet is believed to be accurate. Vertellus Performance Materials Inc. assumes no liability and makes no warranty or representation that the information is correct or complete and EXPRESSLY DISCLAIMS ALL REPRESENTATIONS OR WARRANTIES OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Final determination of suitability of any material and issues of patent infringement is the sole responsibility of the user who alone knows the conditions of intended use. Our customers should ensure that any product incorporating a Vertellus ingredient is safe for its intended use pursuant to applicable law and that any necessary disclosures to consumers have been made.

Vertellus Performance Materials Inc., 2110 High Point Road, Greensboro, NC 27403 USA

USA Tel: 800-227-2436 USA Fax: 336-854-4058 USA Email: VPM-TechServices@vertellus.com

Web: www.vertellus.com